

OIL ANALYSIS REPORT

Area LCAC-81 **LCAC-81 MAIN ENGINES**

3 Lube System Fluid MILITARY MIL-L-23699D (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please note that this is a corrected copy for diagnostic comment updates. Please note that this is a corrected copy for diagnostic comment updates.

Wear


All component wear rates are normal.

Contamination

Discrete particle counts [100 ml] 5-15µm = 107400, 15-25μm = 7500, 25-50μm = 2900, 50-100μm = 100, >100µm = 0. Class 8 There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.




Sample Rating Trend





SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0865228		
Sample Date		Client Info		05 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	0		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	0		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		1882		
Zinc	ppm	ASTM D5185m		0		
Sulfur	ppm	ASTM D5185m		0		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304	>0.05	NEG		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	3299		
Particles >6µm		ASTM D7647	>1300	1179		
Particles >14µm		ASTM D7647	>160	105		
Particles >21µm		ASTM D7647	>40	30		
Particles >38µm		ASTM D7647	>10	1		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/17/14		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.5	1.24		




OIL ANALYSIS REPORT









	VISUAL		method	limit/base	current	history1	history
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
	Appearance	scalar	*Visual	NORML	NORML		
	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPER	RTIES	method	limit/base	current	history1	history
	Visc @ 40°C	cSt	ASTM D445	21.0	25.2		
	SAMPLE IMAG	ES	method	limit/base	current	history1	history
	Color					no image	no image
	00.01						
	_						
	Bottom					no image	no image
	GRAPHS						
	Ferrous Alloys			491,52	Particle Coun	t	
	iron						
mun	6 - nickel			122,880	Severe		
10	4			30,72			
	2			7.68	Abnormal		
	124 L0				N. 1.		
	Apr5/24			Judy 1,920		×	
	Non-ferrous Met	als		Apri5/24 1501 Apri5/24 1511 Million 1511 Apris/24			
	10 copper			5 12		1	
	4			31	0-		
	2-				3-		
	0			24			
	Apr5/24			Apr5/			1
	Viscosity @ 40°0	2			4μ 6μ	14µ 21µ	38µ 71
	Abnormal				Acid Number		
_	26			.1,4,1 (B),10,10,10,10,10,10,10,10,10,10,10,10,10,	Severe		
<u>_</u>	24 - Base			Bu			
. (40°	Base				Abnormal		
52 (40)	20 Abnormal			Acid	Base		
2St (40°	20 Abnormal				4		
202 (40°	18			5/24	2/5		
CSt 140°				Apr5/24	Apr5/24		
CSt 140	18			Apr5/24			
:	WearCheck USA - 5			v, NC 27513		HEK INDUSTRIA	
:	WearCheck USA - 5 WC0865228	Rece	ived : 15	v, NC 27513 5 Apr 2024		1428 N	ICKINLEY A
	WearCheck USA - 5	Rece Teste	ived : 15 ed : 17	v, NC 27513	WALAS	1428 N	

Test Package : PLANT Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: WALNAT [WUSCAR] 06148613 (Generated: 04/24/2024 18:17:35) Rev: 3

Submitted By: SHAWN LAHEY Page 2 of 2

Contact: BOB CLAGETT

T:

F:

bobclagett@walashek.com