


OIL ANALYSIS REPORT

BARRIER DEPARTMENT SAMPLES WEB 16 SF

Gearbox

TEXACO MEROPA 220 (--- GAL)





Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0869543	WC0806399	WC0757227
Sample Date		Client Info		14 Apr 2024	08 Oct 2023	04 Apr 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	<1	0	<1
Chromium	ppm	ASTM D5185m	>15	<1	0	0
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	0	0
Lead	ppm	ASTM D5185m	>100	0	0	<1
Copper	ppm	ASTM D5185m	>200	2	2	2
Tin	ppm	ASTM D5185m	>25	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	3.2	0	0	0
Barium	ppm	ASTM D5185m	0.5	0	0	0
Molybdenum	ppm	ASTM D5185m	1.1	0	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	0.1	2	2	0
Calcium	ppm	ASTM D5185m	1.6	87	43	44
Phosphorus	ppm	ASTM D5185m	159	163	234	243
Zinc	ppm	ASTM D5185m	0.5	16	0	2
Sulfur	ppm	ASTM D5185m	10342	4919	6432	7206
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	10	15	19
Sodium	ppm	ASTM D5185m		3	2	1
Potassium	ppm	ASTM D5185m	>20	1	<1	1
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	1387	7199	932
Particles >6µm		ASTM D7647	>5000	410	1325	281
Particles >14μm		ASTM D7647	>640	56	42	36
Particles >21µm		ASTM D7647	>160	10	10	4
Particles >38µm		ASTM D7647	>40	0	3	0
Particles >71µm		ASTM D7647	>10	0	3	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	18/16/13	20/18/13	17/15/12
FLUID DEGRADA	TION	method	limit/base	current	history1	history2




OIL ANALYSIS REPORT









VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FILLID DOODEDTIES						
FLUID PROPERT	TES .	method			history1	history2


Visc @ 40°C	cSt	ASTM D445	219	203	210	210

SAMPLE IMAGES	method	limit/base	current	history1	histor

Color











Laboratory Sample No.

Lab Number : 06148675 Unique Number : 10978753

: WC0869543

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Apr 2024 **Tested**

Diagnosed

: 16 Apr 2024 : 16 Apr 2024 - Wes Davis

SEALED AIR CORP - CRYOVAC DIVISION 1301 WEST MAGNOLIA AVE

IOWA PARK, TX US 76367 Contact: KEVIN KETCHERSID

T: (940)592-2111

F: (940)592-2513

kevin.a.ketchersid@sealedair.com

Test Package : IND 2 (Additional Tests: PrtCount) Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)