

Area BARRIER DEPARTMENT SAMPLES Machine Io DAVIS STANDARD WEB 08 SF (S/N 6080)

Component Gearbox Fluid

TEXACO MEROPA 220 (3 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend


| SAMPLE INFORM | ΛΑΤΙΟΝ | method | limit/base | current | history1 | history2 |
|------------------|------------|--------------|-------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | WC0913511 | WC0821015 | WC0806407 |
| Sample Date | | Client Info | | 14 Apr 2024 | 08 Oct 2023 | 16 May 2023 |
| Machine Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >200 | <1 | <1 | 2 |
| Chromium | ppm | ASTM D5185m | >15 | <1 | 0 | 0 |
| Nickel | | ASTM D5185m | >15 | 0 | 0 | 0 |
| Titanium | ppm ppm | ASTM D5185m | 210 | 0 | 0 | 0 |
| Silver | | ASTM D5185m | | 0 | 0 | 0 |
| Aluminum | ppm | | >25 | 0 | 4 | 1 |
| Lead | ppm | ASTM D5185m | >25 >100 | 0 | 4 <1 | 0 |
| | ppm | | | 3 | 4 | 5 |
| Copper | ppm | ASTM D5185m | >200 | | | |
| Tin | ppm | ASTM D5185m | >25 | 0 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 3.2 | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | 0.5 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 1.1 | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Magnesium | ppm | ASTM D5185m | 0.1 | <1 | 0 | 0 |
| Calcium | ppm | ASTM D5185m | 1.6 | 1 | 0 | <1 |
| Phosphorus | ppm | ASTM D5185m | 159 | 200 | 320 | 313 |
| Zinc | ppm | ASTM D5185m | 0.5 | 0 | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 10342 | 2274 | 3662 | 3834 |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 1 | 2 | 2 |
| Sodium | ppm | ASTM D5185m | | 1 | <1 | <1 |
| Potassium | ppm | ASTM D5185m | >20 | 0 | 0 | 0 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >20000 | 1012 | 1012 | 393 |
| Particles >6µm | | ASTM D7647 | >5000 | 578 | 554 | 170 |
| Particles >14µm | | ASTM D7647 | >640 | 149 | 129 | 29 |
| Particles >21µm | | ASTM D7647 | >160 | 41 | 28 | 10 |
| Particles >38µm | | ASTM D7647 | >40 | 0 | 1 | 1 |
| Particles >71µm | | ASTM D7647 | >10 | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >21/19/16 | 17/16/14 | 17/16/14 | 16/15/12 |
| FLUID DEGRADA | | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | 0.43 | 0.39 | 0.41 |
| | 0 - 0 | | - | | | |


Report Id: CRYIOW [WUSCAR] 06148706 (Generated: 04/17/2024 21:58:51) Rev: 1


Contact/Location: KEVIN KETCHERSID - CRYIOW




OIL ANALYSIS REPORT










| VISUAL | | method | limit/base | current | history1 | history2 |
|------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERT | IES | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 219 | 158 | 150 | 152 |
| SAMPLE IMAGES | ; | method | limit/base | current | history1 | history2 |
| Color | | | | • | | |
| Bottom | | | | | | |



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 **SEALED AIR CORP - CRYOVAC DIVISION** Sample No. : WC0913511 Received : 15 Apr 2024 1301 WEST MAGNOLIA AVE Lab Number : 06148706 Tested : 16 Apr 2024 IOWA PARK, TX Unique Number : 10978784 Diagnosed : 17 Apr 2024 - Don Baldridge US 76367 Test Package : IND 2 (Additional Tests: PrtCount) Contact: KEVIN KETCHERSID Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. kevin.a.ketchersid@sealedair.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (940)592-2111 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (940)592-2513

Report Id: CRYIOW [WUSCAR] 06148706 (Generated: 04/17/2024 21:58:51) Rev: 1

Contact/Location: KEVIN KETCHERSID - CRYIOW

Page 2 of 2