


OIL ANALYSIS REPORT

PALASYN 45 [8016502] SULLIVAN PALATEK 23DE004000 - CMI

Component Compressor



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCS06148828		
Sample Date		Client Info		09 Apr 2024		
Machine Age	hrs	Client Info		4552		
Oil Age	hrs	Client Info		4552		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0.0	0		
Barium	ppm	ASTM D5185m	0.0	0		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m	0	0		
Magnesium	ppm	ASTM D5185m	0.0	0		
Calcium	ppm	ASTM D5185m	0.0	0		
Phosphorus	ppm	ASTM D5185m	966	540		
Zinc	ppm	ASTM D5185m	0	0		
Sulfur	ppm	ASTM D5185m	1309	998		
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3		
Sodium	ppm	ASTM D5185m		6		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	NOITA	method	limit/base	current	history1	history2
	1/01::					


0.17

Acid Number (AN) mg KOH/g ASTM D8045 0.172

Sullivan

38 34.

OIL ANALYSIS REPORT



VISUAL		method				history2
White Metal	scalar	*Visual	NONE	LIGHT		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TIES	method	limit/base	current	history1	history2

SAMPLE IMAGES	method	limit/base	nistory1	history2
Color		٠	no image	no image
Bottom			no image	no image

42.5

GRAPHS


Visc @ 40°C




cSt

ASTM D445 39.9

8	_		cop	per	Ì.												
		****	lead														
6-	*****	****	tin -) ·												
4-																	
2-																	
بار						 											
Apr9/24																	Anna/74









Certificate 12367

Laboratory

Test Package : IND 2

Sample No. : UCS06148828 Lab Number : 06148828

Unique Number : 10978906

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 15 Apr 2024

Tested : 16 Apr 2024

Diagnosed : 17 Apr 2024 - Sean Felton

SIOUX FALLS, SD US 57104 Contact: REUBEN tim@liftproequipment.com T: (605)339-6494

LIFT PRO EQUIPMENT CO

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)