

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

BC-05 BC-05

Component Gearbox Fluid SCHAEFFER 50W (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0920468		
Sample Date		Client Info		03 Apr 2024		
Machine Age	mths	Client Info		0		
Oil Age	mths	Client Info		12		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	66		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
	ppm	ASTM D5185m	>25	2		
	ppm	ASTM D5185m	>50	<1		
	ppm	ASTM D5185m	>200	0		
	ppm	ASTM D5185m	>10	0		
	ppm	ASTM D5185m		<1		
	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		221		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		7		
Calcium	ppm	ASTM D5185m		3432		
Phosphorus	ppm	ASTM D5185m		945		
Zinc	ppm	ASTM D5185m		1115		
	ppm	ASTM D5185m		6468		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	22		
Sodium	ppm	ASTM D5185m		7		
Potassium	ppm	ASTM D5185m	>20	<1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		



OIL ANALYSIS REPORT



Visc @ 40°C	cSt	ASTM D445		175		
SAMPLE IMAG	ES	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloys			,-			
iron chromium						
)-						
)+						
Apr3/24			Apr3/24 🚰			
			Apri			
Non-ferrous Met	als					
copper measurement lead						
1-						
Apr3/24			Apr3/24			
₹ Viscosity @ 40°			A			
Abnormal						
) = ⁷						
Abnormal						
Abnormal						
*			Apr3/24			
Apr3/24						



Contact/Location: Phil Ivanisin - COVJUN Page 2 of 2