

## **OIL ANALYSIS REPORT**

Sample Rating Trend

# WEAR

EMPE P210-21-1057 (S/N 85/516)

Hydraulic System

TULCO LUBSOIL SUPER HYDRAULIC AW 68 (100 GAL)

### DIAGNOSIS

### A Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

### 📥 Wear

Area

The copper level is abnormal. All other component wear rates are normal.

### Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		TO50002029		
Sample Date		Client Info		10 Apr 2024		
Machine Age	hrs	Client Info		19268		
Oil Age	hrs	Client Info		3697		
Oil Changed		Client Info		Not Changd		
Sample Status				ABNORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>30	1		
Chromium	ppm	ASTM D5185m	>2	0		
Nickel	ppm	ASTM D5185m	>2	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>2	0		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m		× 79		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m	220	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		55		
Calcium	ppm	ASTM D5185m		44		
		ASTM D5185m	425	267		
Phosphorus	ppm					
Zinc	ppm	ASTM D5185m	500	300		
Sulfur	ppm	ASTM D5185m	1900	1614		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	7		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm	ASTM D5185m	>20	0		
Water	%	ASTM D6304		0.004		
ppm Water	ppm	ASTM D6304	>500	40		
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
		ASTM D7647	>5000	<b>6726</b>		
Particles >4µm						
Particles >6µm		ASTM D7647	>1300	535		
Particles >6µm		ASTM D7647 ASTM D7647	>1300 >160	535 10		
Particles >6µm Particles >14µm						
Particles >6μm Particles >14μm Particles >21μm		ASTM D7647	>160	10	  	
Particles >4µm Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647	>160 >40 >10	10 2		
Particles >6μm Particles >14μm Particles >21μm Particles >38μm		ASTM D7647 ASTM D7647 ASTM D7647	>160 >40 >10	10 2 0		
Particles >6µm Particles >14µm Particles >21µm Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	>160 >40 >10 >3	10 2 0 0		



# **OIL ANALYSIS REPORT**



	VISUAL		method	limit/base	current	history1	history
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Apr1 0/24	Appearance	scalar	*Visual	NORML	NORML		
Apr	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history
	Visc @ 40°C	cSt	ASTM D445	67.4	65.4		
	Visc @ 100°C	cSt	ASTM D445	8.8	8.5		
	Viscosity Index (VI)	Scale	ASTM D2270	102	99		
	SAMPLE IMAGES	S	method	limit/base	current	history1	history
Apr10/24	0.000					otory :	
Ap	Color					no image	no image
	Bottom					no image	no image
	GRAPHS						
	Ferrous Alloys				A Particle Count		
Apr10/24	<sup>10</sup> I			491,5			
Apr	8 - iron			122,8	180 -		
	E 4			30,7	Severe		
	2				1		
	24 1 1	*******	**********************	7,6 E 7,6	Abnonnal		
	Apr10/24			Apr10/24 particles (per 1 ml)	120-	•	
	Non-ferrous Metal	s		ticles	180		
	80	5		ţ,		<b>\</b>	
	60 - copper			number	20		
~	톱 40 tin			E	30-		
CUL	20				8-		
~	0	*******	******************		2		
	Apri 0/24			Apr1 0/24	2-		
	✓ Viscosity @ 40°C			A.	0 4μ 6μ	14µ 21µ	38µ 71
	VISCOSILY @ 40°C			Go	Acid Number		
	75 Abnormal			I Number (mg KOH/g)	Base		
	(C) 70 € 5 65			Bu .	60-		
				Der .	40		
	60 - Abnormal			Acid Nu	20		
	55 <del>L  </del>				1/24		
AC OF	Apr10/24			Apr10/24	Apr10/24		
Laboratory Sample No.	: WearCheck USA - 50 : TO50002029 : 06149511	1 Madiso Recei	ived : 15	, NC 27513 5 Apr 2024 5 Apr 2024		1401 NORTH	<b>FABRICATI</b> BOWIE DR HERFORD,

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: JAMWEA [WUSCAR] 06149511 (Generated: 04/17/2024 23:42:52) Rev: 1

Contact/Location: LARRY NORRIS - JAMWEA

F: