

OIL ANALYSIS REPORT

Sample Rating Trend



KAESER ASD 30T 8438391 (S/N 1141)

Component Compressor

Fluid KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. We were unable to perform a particle count due to insufficient sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA017179	KCPA011477	
Sample Date		Client Info		08 Apr 2024	13 Dec 2023	
Machine Age	hrs	Client Info		181	135	
Oil Age	hrs	Client Info		181	0	
Oil Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	ABNORMAL	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	
Chromium	ppm	ASTM D5185m	>10	0	<1	
Nickel	ppm	ASTM D5185m	>3	<1	0	
Titanium	ppm	ASTM D5185m	>3	0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	<1	2	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>50	2	<1	
Tin	ppm	ASTM D5185m	>10	<1	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	
Barium	ppm	ASTM D5185m	90	6	24	
Molybdenum	ppm	ASTM D5185m	0	0	0	
Manganese	ppm	ASTM D5185m		2	0	
Magnesium	ppm	ASTM D5185m	100	68	85	
Calcium	ppm	ASTM D5185m	0	2	2	
Phosphorus	ppm	ASTM D5185m	0	<1	32	
Zinc	ppm	ASTM D5185m	0	<1	0	
Sulfur	ppm	ASTM D5185m	23500	22857	20230	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	
Sodium	ppm	ASTM D5185m		9	3	
Potassium	ppm	ASTM D5185m	>20	32	37	
Water	%	ASTM D6304	>0.05	0.028	0.021	
ppm Water	ppm	ASTM D6304	>500	288	215	
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647			80441	
Particles >6µm		ASTM D7647	>1300		4 9317	
Particles >14µm		ASTM D7647	>80		▲ 3842	
Particles >21µm		ASTM D7647	>20		1 48	
Particles >38µm		ASTM D7647	>4		0	
Particles >71µm		ASTM D7647	>3		0	
Oil Cleanliness		ISO 4406 (c)	>17/13		▲ 23/19	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.37	0.487	



OIL ANALYSIS REPORT





VISUAL						
		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPERTI	ES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45	43.7	44.0	
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						no image
Bottom				•		no image
GRAPHS						
0 Dec13/23			Apr8/24			
Non-ferrous Metals						
6 - copper 6 - tin			24			
Dec13/23			Apr8/2			
Viscosity @ 40°C			Apr8/	Acid Number		
Viscosity @ 40°C				Acid Number		
Viscosity @ 40°C				τ		
Viscosity @ 40°C				τ		
Viscosity @ 40°C				τ		
Viscosity @ 40°C			1.20 HO 0.96 BU 0.72 HO 0.48 U 0.24 U 0.24	Bissormal		
Viscosity @ 40°C			0.120 0.96 0.96 0.72 0.48 0.48 0.24	τ		

- To discuss this sample report, co
- * Denotes test methods that are outside of the ISO 17025 scope of accreditation.
- Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Laboratory

Sample No. Lab Number **Unique Number Test Package**

Contact/Location: R HAAKE - AJCKAN

F: