

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **3016** Component **Hydraulic System** Fluid **AW HYDRAULIC OIL ISO 68 (--- GAL)**

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The oil viscosity is lower than normal. Confirm oil type.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0931857		
Sample Date		Client Info		10 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				ATTENTION		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0		
Chromium	ppm	ASTM D5185m	>20	<1		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	1		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	1		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	<1		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	25	3		
Calcium	ppm	ASTM D5185m	200	38		
Phosphorus	ppm	ASTM D5185m	300	349		
Zinc	ppm	ASTM D5185m	370	418		
Sulfur	ppm	ASTM D5185m	2500	1122		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	3		
Sodium	ppm	ASTM D5185m	210	0		
Potassium	ppm	ASTM D5185m	>20	1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water						
	scalar	^VISUAI	>0.05	NEG		
Free Water	scalar scalar	*Visual *Visual	>0.05	NEG NEG		



OIL ANALYSIS REPORT



	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt A	ASTM D445	68	6 57.4		
SAMPLE IMAG	ÈS	method	limit/base	current	history1	history2
Color					no image	no image
Bottom				A.	no image	no image
GRAPHS						
Ferrous Alloys	tals		Apr10/24			
62 - 60 - 60 - 60 - 60 - 60 - 60 - 60 -						
			Apr10/24			

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Т:

F:

timw@mar-bal.com