OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL

Area
2M34
Machine Id
JTK9528
Component
Diesel Engine
Fluid
DIESEL ENGINE OIL SAE 40 (--- QTS)

DIAGNOSIS

Recommendation
Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear
Metal levels are typical for a new component breaking in.

Contamination
There is no indication of any contamination in the oil.

Fluid Condition
The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**ARI0007523**	ARI0007484	ARI0006846
Sample Date		Client Info		**27 Mar 2024**	28 Dec 2023	19 Oct 2023
Machine Age	mls	Client Info		**18727**	16634	13791
Oil Age	mls	Client Info		**4936**	2843	4815
Oil Changed		Client Info		**Changed**	Changed	Changed
Sample Status				**NORMAL**	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel		WC Method	>5	**<1.0**	<1.0	<1.0
Water		WC Method	>0.2	**NEG**	NEG	NEG
Glycol		WC Method		**NEG**	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	**14**	8	19
Chromium	ppm	ASTM D5185m	>20	**1**	<1	<1
Nickel	ppm	ASTM D5185m	>4	**0**	0	<1
Titanium	ppm	ASTM D5185m		**0**	<1	<1
Silver	ppm	ASTM D5185m	>3	**0**	0	<1
Aluminum	ppm	ASTM D5185m	>20	**12**	6	4
Lead	ppm	ASTM D5185m	>40	**0**	<1	<1
Copper	ppm	ASTM D5185m	>330	**0**	<1	3
Tin	ppm	ASTM D5185m	>15	**<1**	<1	0
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	<1

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	250	**83**	100	388
Barium	ppm	ASTM D5185m	10	**0**	0	4
Molybdenum	ppm	ASTM D5185m	100	**88**	88	92
Manganese	ppm	ASTM D5185m		**0**	0	<1
Magnesium	ppm	ASTM D5185m	450	**93**	120	364
Calcium	ppm	ASTM D5185m	3000	**2110**	1873	1382
Phosphorus	ppm	ASTM D5185m	1150	**979**	1043	1105
Zinc	ppm	ASTM D5185m	1350	**1125**	1153	1216
Sulfur	ppm	ASTM D5185m	4250	**3932**	3630	3488

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	**5**	5	8
Sodium	ppm	ASTM D5185m	>216	**0**	1	0
Potassium	ppm	ASTM D5185m	>20	**7**	8	6

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	**0.3**	0.6	0.4
Nitration	Abs/cm	*ASTM D7624	>20	**9.1**	9.6	7.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	**18.2**	21.0	22.4

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	**13.7**	16.7	16.6
Base Number (BN)	mg KOH/g	ASTM D2896	8.5	**6.8**	7.2	7.8

OIL ANALYSIS REPORT

FT-IR (Direct Trend)



Base Number



Viscosity @ 100°C



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	**NONE**	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	**13.3**	13.0	13.3

GRAPHS

Ferrous Alloys



Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : ARI0007523
Lab Number : 06151495
Unique Number : 10981573
Test Package : CONST (Additional Tests: TBN)

Received : 17 Apr 2024
Tested : 18 Apr 2024
Diagnosed : 18 Apr 2024 - Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

INSITUFORM TECHNOLOGIES, INC
709 EAST ORDNANCE ROAD SUITE 501
BALTIMORE, MD
US 21226
Contact: ALBERT FRIEDRICH
AFRIEDRICH@INSITUFORM.COM
T: (240)388-1832
F: