


OIL ANALYSIS REPORT

ULTRACLEAN GARDNER DENVER S467931 - CARGILL

Component Compressor



Recommendation

Recommend drain oil if not already done and flush with cleaner before refilling with oil. We recommend an early resample to monitor this condition.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is above the recommended limit. TAN level indicates possible presence of varnish.


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06152100		
Sample Date		Client Info		03 Apr 2024		
Machine Age	hrs	Client Info		70004		
Oil Age	hrs	Client Info		20		
Oil Changed		Client Info		N/A		
Sample Status				ATTENTION		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	11		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		1		
Phosphorus	ppm	ASTM D5185m	287	88		
Zinc	ppm	ASTM D5185m		5		
Sulfur	ppm	ASTM D5185m	270	90		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.296	3.99		




OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	33.9	46.1		
SAMPLE IMAGES	3	method	limit/base	current	history1	history2
Color					no image	no image
Bottom					no image	no image



Non	-ferrous	Met						
8	copper	ļ						
E 6-	aaaaaa lead	J						
4								
2			 	 	 	 	 	
Apr3/24								Apr3/24
Visc	osity @	40°C						









Laboratory Sample No.

Lab Number : 06152100

: UCH06152100 Unique Number : 10982178

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Apr 2024

Tested : 19 Apr 2024 Diagnosed : 22 Apr 2024 - Jonathan Hester

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

AIR HANDLING EQUIPMENT INC

1389 RIVERSIDE DR SIDNEY, OH

US 45365

Contact: ANGIE ROSENBECK

angie@ahequip.net T: (937)658-6266

F: (937)492-3147 Contact/Location: ANGIE ROSENBECK - UCAIRSID