


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id **CATERPILLAR 374 10555 (S/N TNX10032)**

Right Final Drive

{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil

Fluid Condition


The condition of the oil is acceptable for the time in service.

L)		Jun2023 Ju	2023 Sep2023 Sep2023	Nov2023 Dec2023 Jan2024 Feb2	024 Apr2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0913235	WC0888138	WC0888223
Sample Date		Client Info		13 Apr 2024	26 Feb 2024	30 Jan 2024
Machine Age	hrs	Client Info		5200	4395	3903
Oil Age	hrs	Client Info		796	492	670
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	17	8	7
Chromium	ppm	ASTM D5185m	>10	2	0	<1
Nickel	ppm	ASTM D5185m	>5	5	2	2
Titanium	ppm	ASTM D5185m	>15	<1	0	<1
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>75	1	<1	2
Lead	ppm	ASTM D5185m	>10	1	0	0
Copper	ppm	ASTM D5185m	>75	19	10	14
Tin	ppm	ASTM D5185m	>8	2	0	<1
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		176	114	176
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		4	10	4
Manganese	ppm	ASTM D5185m		1	0	0
Magnesium	ppm	ASTM D5185m		15	66	19
Calcium	ppm	ASTM D5185m		327	1323	396
Phosphorus	ppm	ASTM D5185m		475	742	597
Zinc	ppm	ASTM D5185m		113	495	129
Sulfur	ppm	ASTM D5185m		2450	3216	2094
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	14	6	4
Sodium	ppm	ASTM D5185m		<1	1	0
Potassium	ppm	ASTM D5185m	>20	3	4	3
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
1 01 E0) D 1				O	C MAILER SAGE	ATT TDANSTI


Contact/Location: MIKE WYATT - TRANEW





OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		101	97.2	104
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image









Laboratory Sample No.

: WC0913235 Lab Number : 06152395 Unique Number : 10982473 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 17 Apr 2024 **Tested** : 18 Apr 2024

Diagnosed : 22 Apr 2024 - Sean Felton

Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

mwyatt@traderconstruction.com T: (252)633-1399

F: (252)638-4871

TRADER CONSTRUCTION CO.

PO DRAWER 1578

Contact: MIKE WYATT

NEW BERN, NC

US 28563