

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

KAESER 8081320

Component Compressor Fluid KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KC122060	KC98568	KC98559
Sample Date		Client Info		29 Jan 2024	15 Dec 2022	17 Mar 2022
Machine Age	hrs	Client Info		12746	7574	2951
Oil Age	hrs	Client Info		0	4623	2951
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				NORMAL	NORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	<1	0
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>10	0	<1	2
Lead	ppm	ASTM D5185m	>10	0	0	<1
Copper	ppm	ASTM D5185m	>50	13	11	3
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	<1
Barium	ppm	ASTM D5185m	90	0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	<1
Manganese	ppm	ASTM D5185m		<1	0	<1
Magnesium	ppm	ASTM D5185m	90	10	15	39
Calcium	ppm	ASTM D5185m	2	1	0	0
Phosphorus	ppm	ASTM D5185m		6	24	<1
Zinc	ppm	ASTM D5185m		70	54	23
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	0
Sodium	ppm	ASTM D5185m		6	6	6
Potassium	ppm	ASTM D5185m	>20	3	7	19
Water	%	ASTM D6304	>0.05	0.013	0.015	0.023
ppm Water	ppm	ASTM D6304	>500	140	157.2	233.3
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		1652	1337	6789
Particles >6µm		ASTM D7647	>1300	456	566	A 3019
Particles >14µm		ASTM D7647	>80	57	20	A 309
Particles >21µm		ASTM D7647	>20	22	4	6 4
Particles >38µm		ASTM D7647	>4	2	1	4
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	18/16/13	18/16/11	▲ 19/15
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.36	0.361	0.37



12000

10000

800 Water (ppm)

6000

4000

2000

u [) 5k 4k 4k

31 2

Ok

12000

0.

52 50

48

() 0€046

لكي 44

42

38

6

saloitades

3

2

0

Vlar1

Mar17/22

Abnom 40

0

OIL ANALYSIS REPORT

NONE

NONE

NONE

NONE

NORML

>0.05

46

NORML

NONE

NONE

NONE

NONE

NONE

NONE

NONE

NONE

NORML


NORML

NEG

NEG

43.8

Water (KF)		VISUAL		method
Severe		White Metal	scalar	*Visual
		Yellow Metal	scalar	*Visual
; •		Precipitate	scalar	*Visual
		Silt	scalar	*Visual
		Debris	scalar	*Visual
Abnormal		Sand/Dirt	scalar	*Visual
Marl 7/22 Dec 15/22	Jan 29/24	Appearance	scalar	*Visual
Mar	Jan	Odor	scalar	*Visual
Particle Trend		Emulsified Water	scalar	*Visual
		Free Water	scalar	*Visual
6μm		FLUID PROPER	TIES	method
		Visc @ 40°C	cSt	ASTM D445
		SAMPLE IMAGE	S	method
Mat 17/22	Jan29/24	Color		
Water (KF)				
Severe		Bottom		
-				
		GRAPHS		
Abnormal		Ferrous Alloys		
Mar17/22 Dec15/22	¥ 6, 0 6	¹⁰ L		
Mar17/22 Dec15/22	C	8 - iron		
		6 - nickel		



NONE

NONE

NONE

NONE

VLITE

NONE

NORML

NORML

NEG

NEG

44.3

NONE

NONE

NONE

NONE

NONE

NONE


NORML

NORML

NEG

NEG

45.2



Report Id: HILSEF [WUSCAR] 06152612 (Generated: 04/23/2024 14:11:01) Rev: 1

Contact/Location: Service Manager - HILSEF Page 2 of 2