

### **OIL ANALYSIS REPORT**

Sample Rating Trend

# NORMAL

Machine Id

# CAPACITY 0807100

Component Rear Hydraulic System

Fluid CHEVRON HYDRAULIC OIL AW ISO 32 (10 GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2		
Sample Number		Client Info		WC0748595	WC0748563	WC0748541		
Sample Date		Client Info		11 Apr 2024	28 Sep 2023	13 Apr 2023		
Machine Age	hrs	Client Info		17984	17158	16549		
Oil Age	hrs	Client Info		6396	5570	4961		
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd		
Sample Status				NORMAL	NORMAL	NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2		
Water		WC Method	>0.1	NEG	NEG	NEG		
WEAR METALS		method	limit/base	current	history1	history2		
Iron	ppm	ASTM D5185m	>20	2	2	2		
Chromium	ppm	ASTM D5185m	>10	1	<1	1		
Nickel	ppm	ASTM D5185m	>10	0	0	0		
Titanium	ppm	ASTM D5185m		0	0	0		
Silver	ppm	ASTM D5185m		0	0	0		
Aluminum	ppm	ASTM D5185m	>10	4	3	5		
Lead	ppm	ASTM D5185m	>10	0	0	0		
Copper	ppm	ASTM D5185m	>75	4	4	4		
Tin	ppm	ASTM D5185m	>10	<1	0	0		
Vanadium	ppm	ASTM D5185m		0	0	0		
Cadmium	ppm	ASTM D5185m		0	0	0		
ADDITIVES		method	limit/base	current	history1	history2		
Boron	ppm	ASTM D5185m		0	0	0		
Barium	ppm	ASTM D5185m		0	0	0		
Molybdenum	ppm	ASTM D5185m		0	0	0		
Manganese	ppm	ASTM D5185m		<1	0	<1		
Magnesium	ppm	ASTM D5185m		0	<1	2		
Calcium	ppm	ASTM D5185m		32	29	39		
Phosphorus	ppm	ASTM D5185m		337	320	311		
Zinc	ppm	ASTM D5185m		392	383	387		
Sulfur	ppm	ASTM D5185m		1136	898	1151		
CONTAMINANTS		method	limit/base	current	history1	history2		
Silicon	ppm	ASTM D5185m	>20	1	<1	<1		
Sodium	ppm	ASTM D5185m		2	<1	1		
Potassium	ppm	ASTM D5185m	>20	2	0	0		
VISUAL		method	limit/base	current	history1	history2		
White Metal	scalar	*Visual	NONE	NONE	LIGHT	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG		
Free Water	scalar	*Visual		NEG	NEG	NEG		
TICC Water	000.00	Contact/Location: CARLOS RENTERIA - DOLSANCA						




## **OIL ANALYSIS REPORT**



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	30.4	45.9	52.0	53.3
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						





Contact/Location: CARLOS RENTERIA - DOLSANCA

Page 2 of 2