

## **OIL ANALYSIS REPORT**

Sample Rating Trend

WEAR

#### Machine Id

SAIR 1 (S/N 003-95315)

Air Compressor

USPI AIR 46 (--- LTR)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### A Wear

An increase in the copper and zinc levels is noted.

#### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		WEAR
ar2017 Aug2017 Ma	y2018 Feb2019 Jan2020 Oct2020 Aug2021 May2022 Apr2023 Jan2024	


SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USPM36744	USPM30706	USPM31117
Sample Date		Client Info		17 Apr 2024	19 Jan 2024	24 Oct 2023
Machine Age	hrs	Client Info		91249	89289	87331
Oil Age	hrs	Client Info		102851	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ATTENTION	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>4	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	0
Lead	ppm	ASTM D5185m	>20	0	0	0
Copper	ppm		>40	<b>A</b> 36	4	<1
Tin	ppm	ASTM D5185m	>5	0	<1	<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	0	0	0	0
Calcium	ppm	ASTM D5185m	0	0	2	0
Phosphorus	ppm	ASTM D5185m	1	0	0	2
Zinc	ppm	ASTM D5185m	0	<u> </u>	19	4
Sulfur	ppm	ASTM D5185m	0	14	0	31
CONTAMINANTS	\$	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	0	0
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	2	0	0
Water	%	ASTM D6304	>0.2	0.050	0.024	0.080
ppm Water	ppm	ASTM D6304	>2000	501	244	802.6
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	2928	7829	196
Particles >6µm		ASTM D7647	>2500	1203	1803	65
Particles >14µm		ASTM D7647	>320	162	60	10
Particles >21µm		ASTM D7647	>80	53	11	2
Particles >38µm		ASTM D7647	>20	3	0	0
Particles >71µm		ASTM D7647	>4	0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	19/17/15	20/18/13	15/13/10
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.05	0.50	0.10	0.077


Contact/Location: - TYSDAKSLA Page 1 of 2





# **OIL ANALYSIS REPORT**














VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	49.7	48.5	47.2	47.0
SAMPLE IMAGES	S	method	limit/base	current	history1	history2

Color



Bottom



Diagnosed : 19 Apr 2024 - Doug Bogart

US Contact:

doug.bogart@wearcheck.com

T: F:

Contact/Location: - TYSDAKSLA