

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

JLG 1255 016-0118 (S/N 0160086959)

Component Rear Right Final Drive

Fluid SCHAEFFER SCHAEFFER 293 MOLY 75W90 (2 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0904103	WC0868328	WC0815021
Sample Date		Client Info		16 Apr 2024	27 Oct 2023	15 Aug 2023
Machine Age	hrs	Client Info		12777	11871	11041
Oil Age	hrs	Client Info		11041	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	l	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	494	408	303
Chromium	ppm	ASTM D5185m	>10	5	4	2
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	2	<1	3
Lead	ppm	ASTM D5185m	>25	<1	0	0
Copper	ppm	ASTM D5185m	>50	16	9	11
Tin	ppm	ASTM D5185m	>10	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		12	10	15
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		243	236	267
Manganese	ppm	ASTM D5185m		9	7	7
Magnesium	ppm	ASTM D5185m		3	<1	2
Calcium	ppm	ASTM D5185m		45	36	64
Phosphorus	ppm	ASTM D5185m		536	459	555
Zinc	ppm	ASTM D5185m		58	57	55
Sulfur	ppm	ASTM D5185m		14741	12295	15279
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	13	7	9
Sodium	ppm	ASTM D5185m		0	1	0
Potassium	ppm	ASTM D5185m	>20	2	<1	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	MODER	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG



OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		96.3	97.6	95.6
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image





Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 Sample No. : WC0904103 Received : 18 Apr 2024 Lab Number : 06153520 Tested : 19 Apr 2024 Unique Number : 10983598 Diagnosed : 19 Apr 2024 - Wes Davis Certificate 12367 Test Package : CONST To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: TECH TECHNICIAN Page 2 of 2

SHIMMICK CONSTRUCTION 5535 TRAILHEAD DRIVE

CHATTANOOGA, TN

Contact: DANIEL LISELLA

daniel.lisella@shimmick.com

US 37415

T:

F: