

OIL ANALYSIS

Machine Id LINE 9 MAIN (SOUTH) (S/N C1 Component Vacuum Pump

USPI VAC 100 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SIS REPO	RT				N	IORMAL
04007000	~ ~ ^`					
C1237000	J34)					
		Jan 2021	Mar2021 Aug2021	Apr2022 Mar2023 J	an2024	
			-			
SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USPM36759	USPM31735	USPM29298
Sample Date		Client Info		18 Apr 2024	02 Jan 2024	19 Aug 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	ATTENTION	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	54	33	50
Chromium	ppm	ASTM D5185m	>20	0	<1	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	0	<1
Lead	ppm	ASTM D5185m	>20	<1	0	0
Copper	ppm	ASTM D5185m	>20	<1	0	<1
Tin	ppm		>20	1	0	<1
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm		0	0	0	4
Barium	ppm		0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	<1	6
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm		0	<1	<1	2
Calcium	ppm	ASTM D5185m		45	70	216
Phosphorus	ppm	ASTM D5185m	1800	889	771	715
Zinc Sulfur	ppm	ASTM D5185m	0	7	22	67
	ppm		0	234	286	1175
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm		>15	6	4	7
Sodium	ppm	ASTM D5185m		14	9	6
Potassium	ppm	ASTM D5185m	>20	2	1	3
Water	%	ASTM D6304	>.1	0.028	0.034	0.040
ppm Water	ppm	ASTM D6304	>1000	284	349	405.3
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	1219	842	
Particles >6µm		ASTM D7647		285	300	
Particles >14µm		ASTM D7647	>160	20	48	
Particles >21µm		ASTM D7647		6	16	
Particles >38µm		ASTM D7647	>10	0	2	
Particles >71µm		ASTM D7647		0	1	
Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/15/11	17/15/13	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
A shell bloom to the bloom	1/01/1		0.05		0 1 0 0	0.05

0.11

Acid Number (AN)

mg KOH/g ASTM D8045 0.05


0.25


0.102


Sample Rating Trend




OIL ANALYSIS REPORT










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	🔺 MODER
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	91	105	108	136
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				•		
						1

Bottom



Test Package : IND 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate 12367

Contact/Location: ? ? - TYSSAI Page 2 of 2

Contact:

T:

F: