

# **OIL ANALYSIS REPORT**

Sample Rating Trend





### Machine Id VOLVO A35F 10333 Component Transmission

Fluid ATF (--- GAL)

#### DIAGNOSIS

## Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


## Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0001427	VCP151341	VCP186753
Sample Date		Client Info		15 Apr 2024	13 Oct 2015	25 Jun 2015
Machine Age	hrs	Client Info		19165	4732	4104
Oil Age	hrs	Client Info		2000	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	14	18	50
Chromium	ppm	ASTM D5185m	>20	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	2	6
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>50	6	12	43
Lead	ppm	ASTM D5185m	>50	0	<1	<1
Copper	ppm	ASTM D5185m		15	9	39
Tin	ppm	ASTM D5185m	>50	<1	0	7
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	ppm			-		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		65	44	155
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		1	<1	1
Manganese	ppm	ASTM D5185m		<1	1	5
Magnesium	ppm	ASTM D5185m		0	<1	5
Calcium	ppm	ASTM D5185m		452	27	205
Phosphorus	ppm	ASTM D5185m		320	126	397
Zinc	ppm	ASTM D5185m		139	33	41
Sulfur	ppm	ASTM D5185m		2908	1608	1698
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	2	3	11
Sodium	ppm	ASTM D5185m		2	3	9
Potassium	ppm	ASTM D5185m	>20	0	8	9
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Energia: field \A/aton						
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar scalar	*Visual *Visual	>0.2	NEG NEG	NEG ted Ry <u>é</u> §ervice	



# **OIL ANALYSIS REPORT**



FLUID PROPER	TIES	method	limit/base	current	history1	histe
Visc @ 40°C	cSt	ASTM D445	35.0	36.0	27.94	28.75
SAMPLE IMAGE	ES	method	limit/base	current	history1	hist
Color				no image	no image	no im
Bottom				no image	no image	no im
GRAPHS						
Ferrous Alloys						
50 45						
40 - nickel						
35						
25 -						
20						
10-						
5 -	a the state of a state of the last of	The Street and in a State of the second second				
5/15	*********	3/15	5/24			
Mar27/14 Jun25/15		0ct13/15	Apr15/24			
Non-ferrous Meta	als					
55 50 copper						
45 - second lead						
40						
30 - 25 -						
25						
15						
10						
0	And and a state of the state of					
Mar27/14 Jun25/15		0ct13/15	Apr15/24			
≥ ⊰ Viscosity @ 40°C		0	Ä			
<sup>65</sup>						
60						
55						
45 40 35 Base						
35 <b>Base</b> 30			and the second se			
25						
20 - Abnormal						
15			24			
Mar27/14 - Jun25/15 -		0ct13/15	Apr15/24			



Submitted By: Service - Alex Anderson Page 2 of 2