


# **OIL ANALYSIS REPORT**

# **NOT GIVEN [285016]** KAISHAN K302003803U - FAB FOUR

Component



### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.


### **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UFD0001587		
Sample Date		Client Info		11 Apr 2024		
Machine Age	hrs	Client Info		19458		
Oil Age	hrs	Client Info		5333		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		<1		
Phosphorus	ppm	ASTM D5185m		6		
Zinc	ppm	ASTM D5185m		<1		
Sulfur	ppm	ASTM D5185m		0		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.23		



## **OIL ANALYSIS REPORT**









Certificate 12367

Laboratory Sample No.

Lab Number : 06156122

(40°C)

: UFD0001587 Unique Number : 10991545 Test Package : IND 2

Apr11/24

Viscosity @ 40°C

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Apr 2024 **Tested** : 23 Apr 2024

Diagnosed

: 24 Apr 2024 - Sean Felton

Apr11/24

FLUID-AIRE DYNAMICS - (MN)

14250 JUDICIAL ROAD BURNSVILLE, MN US 55306

Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: Service Manager - UCFLUBUR

Acid Number

0.25 NO 0.20

£ 0.15 은 0.10 0.05 0.00

T:

F: