


OIL ANALYSIS REPORT

Sample Rating Trend







CS-46 [PM6-3002221] KAESER 1169 - PROPAK

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
|------------------|----------|-------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | UCH06156149 | UCH05933767 | UCH05744715 |
| Sample Date | | Client Info | | 11 Apr 2024 | 11 Jul 2023 | 06 Jan 2023 |
| Machine Age | hrs | Client Info | | 73321 | 70814 | 69328 |
| Oil Age | hrs | Client Info | | 2507 | 5000 | 3913 |
| Oil Changed | | Client Info | | Not Changd | Changed | Not Changd |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATION | V | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.05 | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >50 | <1 | <1 | 0 |
| Chromium | ppm | ASTM D5185m | >10 | <1 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | >3 | <1 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | >3 | <1 | 0 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >10 | 2 | 0 | 0 |
| Lead | ppm | ASTM D5185m | >10 | 0 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >50 | <1 | 0 | <1 |
| Tin | ppm | ASTM D5185m | >10 | <1 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 1.5 | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | 0 | 1 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 0 | <1 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | 0.3 | 0 | 0 | 0 |
| Magnesium | ppm | ASTM D5185m | 0 | <1 | <1 | 0 |
| Calcium | ppm | ASTM D5185m | 0 | <1 | 2 | 0 |
| Phosphorus | ppm | ASTM D5185m | 406 | 180 | 184 | 171 |
| Zinc | ppm | ASTM D5185m | 0 | <1 | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 1283 | 1466 | 2247 | 1620 |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 5 | 3 | 3 |
| Sodium | ppm | ASTM D5185m | | <1 | 0 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | <1 | 0 | <1 |
| FLUID DEGRADA | ATION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | 0.463 | 0.06 | 0.136 | 0.10 |





OIL ANALYSIS REPORT



| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|-----------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | LIGHT |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | LIGHT | LIGHT | MODER |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |
| FLUID PROPERTIES | | method | limit/base | current | history1 | history2 |
| Visc @ 40°C | cSt | ASTM D445 | 47.9 | 45.6 | 47.9 | 45.1 |
| SAMPLE IMAGES | | method | limit/base | current | history1 | history2 |
| | | | | | | |











Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Lab Number : 06156149 $\textbf{Unique Number} \quad : 10991572$

: UCH06156149

Color

Bottom

Received **Tested**

: 22 Apr 2024 : 23 Apr 2024

Diagnosed : 24 Apr 2024 - Sean Felton

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

CISCO AIR SYSTEMS

214 27TH ST SACRAMENTO, CA US 95816

Contact: BARRY FRKOVICH barryfrkovich@ciscoair.com

T: (916)444-2525 F: x:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)