


# **OIL ANALYSIS REPORT**

Sample Rating Trend



**NORMAL** 



Machine Id

# **SULLAIR 201402250074 - CPP**

Compressor

**QUINCY QUINSYN PG (--- QTS)** 

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the

### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM | IATION | method      | limit/base | current     | history1    | history2     |
|---------------|--------|-------------|------------|-------------|-------------|--------------|
| Sample Number |        | Client Info |            | WC0920573   | WC0608961   | WC05257460   |
| Sample Date   |        | Client Info |            | 14 Apr 2024 | 28 Mar 2022 | 10 Dec 2020  |
| Machine Age   | hrs    | Client Info |            | 26525       | 12983       | 8370         |
| Oil Age       | hrs    | Client Info |            | 1848        | 4505        | 0            |
| Oil Changed   |        | Client Info |            | Not Changd  | N/A         | N/A          |
| Sample Status |        |             |            | NORMAL      | MARGINAL    | SEVERE       |
| CONTAMINATION | ١      | method      | limit/base | current     | history1    | history2     |
| Water         |        | WC Method   | >0.1       | NEG         | NEG         | NEG          |
| WEAR METALS   |        | method      | limit/base | current     | history1    | history2     |
| Iron          | ppm    | ASTM D5185m | >50        | 3           | 4           | <b>△</b> 130 |
| Chromium      | ppm    | ASTM D5185m | >10        | <1          | 0           | <1           |
| Nickel        | ppm    | ASTM D5185m |            | <1          | 0           | <1           |
| Titanium      | ppm    | ASTM D5185m |            | <1          | 0           | 0            |
| Silver        | ppm    | ASTM D5185m |            | 0           | 0           | <1           |
| Aluminum      | ppm    | ASTM D5185m | >25        | 2           | <1          | <1           |
| Lead          | ppm    | ASTM D5185m | >25        | 0           | <1          | 2            |
| Copper        | ppm    | ASTM D5185m | >50        | 3           | 17          | 9            |
| Tin           | ppm    | ASTM D5185m | >15        | <1          | <1          | 1            |
| Antimony      | ppm    | ASTM D5185m |            |             |             | 0            |
| Vanadium      | ppm    | ASTM D5185m |            | <1          | 0           | 0            |
| Cadmium       | ppm    | ASTM D5185m |            | <1          | 0           | <1           |
| ADDITIVES     |        | method      | limit/base | current     | history1    | history2     |
| Boron         | ppm    | ASTM D5185m |            | <1          | <1          | 9            |
| Barium        | ppm    | ASTM D5185m |            | 650         | 585         | 181          |
| Molybdenum    | ppm    | ASTM D5185m |            | <1          | 0           | <1           |
| Manganese     | ppm    | ASTM D5185m |            | <1          | <1          | <1           |
| Magnesium     | ppm    | ASTM D5185m |            | 2           | 0           | 2            |
| Calcium       | ppm    | ASTM D5185m |            | 5           | 2           | 10           |
| Phosphorus    | ppm    | ASTM D5185m |            | 21          | 23          | 9            |
| Zinc          | ppm    | ASTM D5185m |            | 8           | 20          | 3            |
| Sulfur        | ppm    | ASTM D5185m |            | 393         | 342         | 293          |
| CONTAMINANTS  |        | method      | limit/base | current     | history1    | history2     |
| Silicon       | ppm    | ASTM D5185m | >25        | 1           | <1          | <1           |
| Sodium        | ppm    | ASTM D5185m |            | 88          | 57          | 13           |
| Potassium     | ppm    | ASTM D5185m | >20        | 5           | 2           | 4            |
| FLUID DEGRADA | TION   | method      | limit/base | current     | history1    | history2     |
|               |        |             |            |             |             |              |

0.85

Acid Number (AN)


mg KOH/g ASTM D8045

0.41


**3.762** 



## **OIL ANALYSIS REPORT**



| \/(OLIA)                |        |           | 11 1.0     |         |          |          |
|-------------------------|--------|-----------|------------|---------|----------|----------|
| VISUAL                  |        | method    | limit/base | current | history1 | history2 |
| White Metal             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal            | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Precipitate             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Silt                    | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Debris                  | scalar | *Visual   | NONE       | NONE    | ▲ MODER  | ▲ MODER  |
| Sand/Dirt               | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Appearance              | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Odor                    | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| <b>Emulsified Water</b> | scalar | *Visual   | >0.1       | NEG     | NEG      | ▲ 0.2%   |
| Free Water              | scalar | *Visual   |            | NEG     | NEG      | NEG      |
| FLUID PROPERT           | TES    | method    | limit/base | current | history1 | history2 |
| Visc @ 40°C             | cSt    | ASTM D445 | 41.9       | 49.5    | 46.7     | 46.5     |
| SAMPLE IMAGES           | 3      | method    | limit/base | current | history1 | history2 |
| Color                   |        |           |            | OF WALL |          |          |
| Bottom                  |        |           |            |         |          |          |







Certificate 12367

Laboratory Sample No.

Test Package : IND 2

Lab Number : 06156166

: WC0920573 Unique Number : 10991589

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Apr 2024

**Tested** : 23 Apr 2024 Diagnosed

: 24 Apr 2024 - Sean Felton

JOHN HENRY FOSTER MINNESOTA INC.

3103 MIKE COLLINS DRIVE EAGAN, MN

US 55121 Contact: MARTY ADAM marty.adam@jhfoster.com

T: (651)681-5745 F: (651)681-0536

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)