

OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



CRANE - T LANGE T LANGE

Component **Port Genset**

CHEVRON DELO 400 LE 15W40 (5 GAL)

וט	Δ	CI)	м	$\overline{}$	115
_		\sim 1	N	${}^{\circ}$	

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0785601	WC0892617	WC0892613
Sample Date		Client Info		09 Mar 2024	14 Feb 2024	24 Jan 2024
Machine Age	hrs	Client Info		52109	36529	36320
Oil Age	hrs	Client Info		250	250	230
Oil Changed		Client Info		Changed	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	1	method	limit/base	current	history1	history2
Fuel		WC Method	>4.0	<1.0	<1.0	<1.0
Water		WC Method	>0.1	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	4	4	<1
Chromium	ppm	ASTM D5185m	>4	<1	<1	0
Nickel	ppm	ASTM D5185m	>2	<1	<1	<1
Titanium	ppm	ASTM D5185m		<1	<1	<1
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	5	4	4
Lead	ppm	ASTM D5185m	>17	0	0	0
Copper	ppm	ASTM D5185m	>70	<1	<1	0
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Vanadium	ppm	ASTM D5185m		<1	<1	<1
Cadmium	ppm	ASTM D5185m		<1	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		342	349	387
Barium	ppm	ASTM D5185m		<1	<1	0
Molybdenum	ppm	ASTM D5185m		130	124	117
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		648	643	655
Calcium	ppm	ASTM D5185m		1555	1517	1457
Phosphorus	ppm	ASTM D5185m	1200	684	693	686
Zinc	ppm	ASTM D5185m	1300	851	853	836
Sulfur	ppm	ASTM D5185m	3200	2524	2640	2486
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	5	5
Sodium	ppm	ASTM D5185m		2	2	<1
Potassium	ppm	ASTM D5185m	>20	2	2	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.2	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	6.2	5.3	4.6
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.4	22.1	22.2
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.1	15.5	15.2
Base Number (BN)	mg KOH/g	ASTM D2896	9.6	9.6	9.7	9.8
	0 0					



OIL ANALYSIS REPORT











VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG

FLUID PROPER	TIES	method				history2
Visc @ 100°C	cSt	ASTM D445	15.7	12.9	13.3	13.7













Laboratory Sample No.

: WC0785601 Lab Number : 06156597 Unique Number : 10992020

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Apr 2024

Tested : 23 Apr 2024 Diagnosed : 23 Apr 2024 - Wes Davis

CONVENT, LA US 70723 Contact: GREG JOSEY gjosey@associatedterminals.com

Test Package : FLEET Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (225)562-3515 Contact/Location: GREG JOSEY - STJCONKL

ASSOCIATED TERMINALS - CRANE

T: