

## **OIL ANALYSIS REPORT**

Sample Rating Trend

ISO

### Machine Id KAESER SK 15 4851069 (S/N 1532)

Component Compressor Fluid

KAESER SIGMA (OEM) S-460 (--- QTS)

#### DIAGNOSIS

#### Recommendation

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

#### Contamination

There is a high amount of particulates present in the oil.

#### Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA012548	KCPA006553	KCPA004330
Sample Date		Client Info		17 Apr 2024	04 Jan 2024	18 Aug 2023
Machine Age	hrs	Client Info		37891	36636	35048
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Changed	N/A	N/A
Sample Status				ABNORMAL	ABNORMAL	SEVERE
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	<1	0
Chromium	ppm	ASTM D5185m	>10	<1	<1	0
Nickel	ppm	ASTM D5185m	>3	<1	0	0
Titanium	ppm	ASTM D5185m	>3	<1	0	<1
Silver	ppm	ASTM D5185m	>2	<1	0	0
Aluminum	ppm	ASTM D5185m	>10	3	2	3
Lead	ppm	ASTM D5185m	>10	ء <1	0	0
Copper	ppm	ASTM D5185m	>50	4	6	8
Tin	ppm	ASTM D5185m	>10	- <1	0	0
Vanadium	ppm	ASTM D5185m	210	<1	0	0
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	20	0	0
Molybdenum	ppm	ASTM D5185m	00	<1	0	0
Manganese	ppm	ASTM D5185m		<1	0	0
Magnesium	ppm	ASTM D5185m	90	61	27	<1
Calcium	ppm	ASTM D5185m	2	0	0	<1
Phosphorus	ppm	ASTM D5185m	-	0	38	2
Zinc	ppm	ASTM D5185m		5	0	0
Sulfur	ppm	ASTM D5185m		J 19487	20498	20883
CONTAMINANTS	ppm	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		2	<1	<1
Sodium	ppm	ASTM D5185m	220	12	7	4
Potassium	ppm	ASTM D5185m	>20	4	2	<1
Water	%	ASTM D5185III		4	0.016	▲ 1.03
vvaler			>0.00	0.020	0.010	1.00
opm Water	ppm	ASTM D6304	>500	208	165	<b>1</b> 0300
ppm Water FLUID CLEANLIN	ppm ESS	ASTM D6304 method	>500 limit/base	208 current	165 history1	▲ 10300 history2
FLUID CLEANLIN						
ppm Water FLUID CLEANLIN Particles >4µm Particles >6µm		method	limit/base	current	history1	history2
FLUID CLEANLIN Particles >4μm Particles >6μm		method ASTM D7647	limit/base	current 23711	history1 36431	history2
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm		method ASTM D7647 ASTM D7647 ASTM D7647	limit/base	current 23711 ▲ 5767 ▲ 347	history1 36431 ▲ 17189	history2
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm		method ASTM D7647 ASTM D7647	limit/base >1300 >80	current 23711 ▲ 5767	history1 36431 ▲ 17189 ▲ 4049	history2  
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >1300 >80 >20 >4	current     23711     ▲ 5767     ▲ 347     ▲ 97	history1 36431 ▲ 17189 ▲ 4049 ▲ 1174	history2   
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm		method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >1300 >80 >20	current   23711   ▲ 5767   ▲ 347   ▲ 97   6	history1 36431 ▲ 17189 ▲ 4049 ▲ 1174 ▲ 44	history2   
FLUID CLEANLIN Particles >4μm Particles >6μm Particles >14μm Particles >21μm Particles >38μm Particles >71μm	ESS	method ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647 ASTM D7647	limit/base >1300 >80 >20 >4 >3	current   23711   ▲ 5767   ▲ 347   ▲ 97   6   0	history1 36431 ▲ 17189 ▲ 4049 ▲ 1174 ▲ 44 2	history2


Contact/Location: J. SARTIN - ASSTUR Page 1 of 2



# **OIL ANALYSIS REPORT**








Abnorma 40

38

Mar28/15

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	🔺 HEAVY
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	▲ 0.2%
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	45.5	44.9	44.4
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color					. 8	
Bottom						



Report Id: ASSTUR [WUSCAR] 06156918 (Generated: 04/24/2024 17:25:38) Rev: 1

Contact/Location: J. SARTIN - ASSTUR Page 2 of 2