

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id

54960 - L&W SUPPLY

Hydraulic System AW HYDRAULIC OIL ISO 32 (--- GAL)

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


				Aprzuz4		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0897208		
Sample Date		Client Info		22 Apr 2024		
Machine Age	mls	Client Info		0		
Dil Age	mls	Client Info		0		
Dil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	1	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
ron	ppm	ASTM D5185m	>20	2		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>10	2		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>75	1		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	1		
Vanganese	ppm	ASTM D5185m		0		
Vagnesium	ppm	ASTM D5185m	25	10		
Calcium	ppm	ASTM D5185m	200	117		
Phosphorus	ppm	ASTM D5185m	300	337		
Zinc	ppm	ASTM D5185m	370	460		
Sulfur		ASTM D5185m	2500	1178		
	ppm			1178		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	2		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	2958		
Particles >6µm		ASTM D7647	>1300	394		
Particles >14µm		ASTM D7647	>160	22		
Particles >21µm		ASTM D7647	>40	6		
Particles >38µm		ASTM D7647	>10	0		
Particles >71µm		ASTM D7647		0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/16/12		
FLUID DEGRADA		method	limit/base	current		
					history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.47		
40·06) Rev: 1				Contac	t/Location: FRI	CHILL - PAL

Report Id: PALTIF [WUSCAR] 06157588 (Generated: 04/24/2024 10:40:06) Rev: 1


Contact/Location: ERIC HILL - PALTIF Page 1 of 2



OIL ANALYSIS REPORT







5 21

n, Apr22/2

NONE White Metal *Visual NONE scalar Yellow Metal *Visual NONE NONE scalar NONE Precipitate scalar *Visual NONE Silt scalar *Visual NONE NONE Debris *Visual NONE scalar NONE Sand/Dirt NONE NONE scalar *Visual NORML NORML Appearance scalar *Visual Odor *Visual NORML NORML scalar **Emulsified Water** scalar *Visual >0.1 NEG Free Water scalar *Visual NEG FLUID PROPERTIES 32.6 Visc @ 40°C cSt ASTM D445 32 SAMPLE IMAGES Color no image no image Bottom no image no image GRAPHS Ferrous Alloys Particle Count 491,52 122,88 30.72 7.68 Apr22/24 4406 per 1 1.920 :1999 Cle Non-ferrous Metals 480 120 14 maa 31 214 Viscosity @ 40°C Acid Number 40 1.00 (B/H0) 0.80 K0H/0 Abnor (40°C) Ë 0.60 Ba . 중 30 · 은 0.40 Abno Acid Ni 0.20 25 0.00 Apr22/24 Anr77/74 0100rul

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513 **PALFINGER - BRANCH 400** Sample No. : WC0897208 Received : 23 Apr 2024 4151 W ST RT 18 Lab Number : 06157588 Tested : 24 Apr 2024 TIFFIN, OH Unique Number : 10993011 Diagnosed : 24 Apr 2024 - Wes Davis US 44883 Test Package : CONST Contact: ERIC HILL Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. e.hill@palfinger.com * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. T: (419)448-8156 E:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: ERIC HILL - PALTIF

Page 2 of 2