

## **OIL ANALYSIS REPORT**

Sample Rating Trend





VOLVO EC480E 310963 Component Hydraulic System

Fluid {not provided} (--- GAL)

## DIAGNOSIS

#### Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

### Wear

All component wear rates are normal.

### Contamination

There is a moderate amount of visible silt present in the sample.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0000971		
Sample Date		Client Info		22 Apr 2024		
Machine Age	hrs	Client Info		8775		
Oil Age	hrs	Client Info		8775		
Oil Changed		Client Info		N/A		
Sample Status				ABNORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>25	11		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	<1		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>150	21		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		79		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		6		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		43		
Calcium	ppm	ASTM D5185m		2862		
Phosphorus	ppm	ASTM D5185m		945		
Zinc	ppm	ASTM D5185m		1199		
Sulfur	ppm	ASTM D5185m		7053		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	9		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	ma KOH/a	ASTM D8045		0.88		



# **OIL ANALYSIS REPORT**

method

limit/base

current

historv1

historv2

VISUAL



	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE				
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
	Appearance	scalar	*Visual	NORML	NORML			
	dor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445		44.8			
	SAMPLE IMAG	ES	method	limit/base	current	history1	history2	
	Color					no image	no image	
	Bottom					no image	no image	
	Non-ferrous Me	tals		Apr22/24				
	Viscosity @ 40° Abnormal Abnormal Abnormal Abnormal Abnormal Abnormal Abnormal Abnormal	C		2/2/4 Acid Number (ng KOH(d)	Acid Numbe	r		
Laborator Sample N Lab Numb Unique Num Test Packa ccuss this sample rep	i i   y : WearCheck USA - !   o. : ML0000971   per : 06159004   ber : 10994427   nge : CONST   port, contact Customer Se	501 Madiso Recei Teste Diagr	n Ave., Cary ived : 24 d : 25 nosed : 25	₹ , NC 27513 Apr 2024 Apr 2024 Apr 2024 - Do	ē n Baldridge	WILLIAM HAZE PO BOX 60 CHANTILLY, V US 2015 Contact: SERVICE MANAGE jimmy_elswick@wahazel.coi T: (703)378-830		

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Service - William Brittle