


OIL ANALYSIS REPORT

FILMS DEPARTMENT SAMPLES DAVIS STAND 5B (S/N P2972) Component Gearbox

TEXACO REGAL OIL R&O 220 (15 GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	MATION	method	limit/base	ourront	history1	history2
	IATION		IIIIII/Dase		· ·	•
Sample Number Sample Date		Client Info		WC0869531 23 Apr 2024	WC0821023 08 Oct 2023	WC0757274
Machine Age	hrs	Client Info		23 Apr 2024 0	06 OCI 2023	04 Apr 2023 0
Oil Age	hrs	Client Info		0	0	0
Oil Changed	1113	Client Info		N/A	N/A	N/A
Sample Status		Oliciti iiilo		NORMAL	NORMAL	NORMAL
CONTAMINATION	,	method	limit/base	current	history1	history2
Water	V	WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
					•	,
Iron	ppm	ASTM D5185m	>200	5	4	7
Chromium	ppm	ASTM D5185m		0	0	0
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	0.5	0	0	0
Aluminum	ppm	ASTM D5185m		0	0	0
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>200	4	3	5
Tin	ppm	ASTM D5185m	>25	0	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	3	2	3
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	0	0	3	0
Calcium	ppm	ASTM D5185m	0	9	14	11
Phosphorus	ppm	ASTM D5185m	0	152	162	157
Zinc	ppm	ASTM D5185m	0	18	5	12
Sulfur	ppm	ASTM D5185m	4046	7722	6621	7408
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	0	1	2
Sodium	ppm	ASTM D5185m		3	2	1
Potassium	ppm	ASTM D5185m	>20	0	<1	1
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>20000	608	6599	1386
Particles >6µm		ASTM D7647	>5000	326	1387	954
Particles >14µm		ASTM D7647	>640	46	122	308
Particles >21µm		ASTM D7647	>160	5	23	36
Particles >38µm		ASTM D7647	>40	0	2	2
Particles >71µm		ASTM D7647	>10	0	1	0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	16/16/13	20/18/14	18/17/15
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
A sial Niversland (ANI)	I/OLI/-	4 OTM D0045		0.44	0.00	0.20




OIL ANALYSIS REPORT









VISUAL		method				history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2

T LOID I HOI LITT						
Visc @ 40°C	cSt	ASTM D445	220	167	165	163


Color

Bottom













Certificate 12367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0869531

Lab Number : 06159047 Unique Number : 10994470

Test Package : IND 2 (Additional Tests: PrtCount)

Received **Tested** Diagnosed

: 24 Apr 2024 : 25 Apr 2024 : 25 Apr 2024 - Don Baldridge

1301 WEST MAGNOLIA AVE IOWA PARK, TX US 76367

Contact: KEVIN KETCHERSID kevin.a.ketchersid@sealedair.com

SEALED AIR CORP - CRYOVAC DIVISION

T: (940)592-2111 F: (940)592-2513

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)