




# OIL ANALYSIS REPORT

Sample Rating Trend



**NORMAL**



Area  
**FILMS DEPARTMENT SAMPLES**  
 Machine Id  
**DAVIS STAND 6A (S/N R4012)**  
 Component  
**Gearbox**  
 Fluid  
**TEXACO REGAL OIL R&O 220 (25 GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>WC0869534</b>	WC0821032	WC0757278
Sample Date	Client Info			<b>23 Apr 2024</b>	08 Oct 2023	04 Apr 2023
Machine Age	hrs	Client Info		<b>0</b>	0	0
Oil Age	hrs	Client Info		<b>0</b>	0	0
Oil Changed	Client Info			<b>N/A</b>	N/A	N/A
Sample Status				<b>NORMAL</b>	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method		>0.2	<b>NEG</b>	NEG	NEG





WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	<b>46</b>	41	34
Chromium	ppm	ASTM D5185m	>15	<b>0</b>	0	0
Nickel	ppm	ASTM D5185m	>15	<b>0</b>	0	0
Titanium	ppm	ASTM D5185m		<b>0</b>	0	0
Silver	ppm	ASTM D5185m		<b>0</b>	0	0
Aluminum	ppm	ASTM D5185m	>25	<b>0</b>	3	0
Lead	ppm	ASTM D5185m	>100	<b>0</b>	<1	<1
Copper	ppm	ASTM D5185m	>200	<b>15</b>	15	20
Tin	ppm	ASTM D5185m	>25	<b>0</b>	0	0
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	0
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<b>0</b>	1	3
Barium	ppm	ASTM D5185m	0	<b>0</b>	0	0
Molybdenum	ppm	ASTM D5185m	0	<b>0</b>	<1	1
Manganese	ppm	ASTM D5185m		<b>0</b>	<1	<1
Magnesium	ppm	ASTM D5185m	0	<b>&lt;1</b>	0	0
Calcium	ppm	ASTM D5185m	0	<b>4</b>	2	<1
Phosphorus	ppm	ASTM D5185m	0	<b>204</b>	235	175
Zinc	ppm	ASTM D5185m	0	<b>16</b>	0	15
Sulfur	ppm	ASTM D5185m	4046	<b>7023</b>	6421	7207

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	<b>4</b>	6	9
Sodium	ppm	ASTM D5185m		<b>5</b>	5	4
Potassium	ppm	ASTM D5185m	>20	<b>0</b>	<1	<1

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		<b>957</b>	4873	2078
Particles >6µm		ASTM D7647	>5000	<b>361</b>	950	404
Particles >14µm		ASTM D7647	>640	<b>88</b>	72	33
Particles >21µm		ASTM D7647	>160	<b>15</b>	17	7
Particles >38µm		ASTM D7647	>40	<b>0</b>	1	1
Particles >71µm		ASTM D7647	>10	<b>0</b>	1	0
Oil Cleanliness		ISO 4406 (c)	>--/19/16	<b>17/16/14</b>	19/17/13	18/16/12


FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		<b>0.59</b>	0.54	0.68








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	220	184	186

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : WC0869534  
**Lab Number** : 06159057  
**Unique Number** : 10994480  
**Test Package** : IND 2 ( Additional Tests: PrtCount )

**Received** : 24 Apr 2024  
**Tested** : 25 Apr 2024  
**Diagnosed** : 25 Apr 2024 - Don Baldrige

**SEALED AIR CORP - CRYOVAC DIVISION**  
 1301 WEST MAGNOLIA AVE  
 IOWA PARK, TX  
 US 76367

Contact: KEVIN KETCHERSID  
 kevin.a.ketchersid@sealedair.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.  
 \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.  
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (940)592-2111  
 F: (940)592-2513