

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area NOT GIVEN QUINCY API851006 - AMCOR

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06159253		
Sample Date		Client Info		23 Mar 2024		
Machine Age	hrs	Client Info		33315		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	1		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		12		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		5		
Phosphorus	ppm	ASTM D5185m		<1		
Zinc	ppm	ASTM D5185m		2		
Sulfur	ppm	ASTM D5185m		0		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1		
Sodium	ppm	ASTM D5185m		15		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.32		



OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Mar23/24	Appearance	scalar	*Visual	NORML	NORML		
Mar2	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.1	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IFS	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	innibacco	51.8		
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Mar23/24 +	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metal	S		Mat23/24			
	Mar23/24			Mar23/24 -			
	Viscosity @ 40°C			_	Acid Number		
	50 Abnormal 50 Abnormal 40 Abnormal 35			(0.4(0.1(0) 0.10) 0.2(0.1(0)			
Laboratory	· WoorChook USA 50	1 Madia		WC 27513	COMDI 1	TE ENGINEERED S	
Sample No. Lab Number Unique Number Test Package discuss this sample report, Denotes test methods that	: 10994676 : IND 2 , contact Customer Servi	Rece Teste Diagi ice at 1-8 7025 sco	ived : 24 ed : 25 nosed : 26 800-237-1365 ope of accred	Apr 2024 5 Apr 2024 Apr 2024 - Jonat 9. <i>litation.</i>	47 han Hester	72 FRONTIER S S Contact: CHRIS christo@c T:	WAY UNIT 40 TOCKTON, C US 9521

Report Id: UCCOMSTO [WUSCAR] 06159253 (Generated: 04/26/2024 10:04:10) Rev: 1

Contact/Location: CHRISTO GINGRAS - UCCOMSTO