

OIL ANALYSIS REPORT

_









VOLVO A30G 340072
Component Front Axle

GEAR OIL SAE 80W140 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM			,			
Sample Number	IATION	method	limit/base	current	history1	history2
		Client Info		ML0000987		
Sample Date		Client Info		22 Apr 2024		
lachine Age	hrs	Client Info		11356		
il Age	hrs	Client Info		11356		
il Changed		Client Info		N/A		
ample Status				NORMAL		
CONTAMINATION	1	method	limit/base	current	history1	history2
Vater		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
on	ppm	ASTM D5185m	>900	37		
hromium	ppm	ASTM D5185m	>20	0		
lickel	ppm	ASTM D5185m	>10	0		
itanium	ppm	ASTM D5185m		0		
ilver	ppm	ASTM D5185m		0		
luminum	ppm		>30	0		
ead		ASTM D5185m	>50	0		
copper	ppm		>150	0		
in	ppm		>150			
	ppm	ASTM D5185m	>20	<1		
anadium	ppm	ASTM D5185m		0		
admium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
oron	ppm	ASTM D5185m	400	168		
arium	ppm	ASTM D5185m	200	0		
lolybdenum	ppm	ASTM D5185m	12	0		
langanese	ppm	ASTM D5185m		<1		
lagnesium	ppm	ASTM D5185m	12	12		
alcium	ppm	ASTM D5185m	150	84		
hosphorus	ppm	ASTM D5185m	1650	1008		
inc	ppm	ASTM D5185m	125	42		
ulfur	ppm	ASTM D5185m	22500	32678		
CONTAMINANTS		method	limit/base	current	history1	history2
	nnm				,	,
ilicon	ppm	ASTM D5185m	>500	3		
odium	ppm	ASTM D5185m	00	0		
	ppm	ASTM D5185m		<1		
					history1	history2
VISUAL		method		current	History	111010172
	scalar	*Visual	NONE	NONE		
VISUAL /hite Metal	scalar scalar	*Visual				
VISUAL /hite Metal ellow Metal		*Visual	NONE	NONE		
VISUAL /hite Metal ellow Metal recipitate	scalar	*Visual	NONE NONE	NONE NONE		
VISUAL /hite Metal ellow Metal recipitate ilt	scalar scalar	*Visual *Visual *Visual	NONE NONE	NONE NONE NONE		
VISUAL /hite Metal ellow Metal recipitate ilt ebris	scalar scalar scalar	*Visual *Visual *Visual *Visual	NONE NONE NONE	NONE NONE NONE LIGHT		
VISUAL	scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE	NONE NONE NONE LIGHT NONE		
VISUAL /hite Metal ellow Metal recipitate ilt ebris and/Dirt ppearance	scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE NONE	NONE NONE NONE LIGHT NONE NONE		
VISUAL /hite Metal ellow Metal recipitate ilt ebris and/Dirt	scalar scalar scalar scalar scalar scalar	*Visual *Visual *Visual *Visual *Visual *Visual *Visual *Visual	NONE NONE NONE NONE NONE NONE NONE NORML	NONE NONE LIGHT NONE NONE NONE		




OIL ANALYSIS REPORT




FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	263	297		
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
CDADHS						

Ferrous Alloys



Non-ferrous Metals



320	Viscosity @ 40°C	
300		
280		
cSt (40°C)	Base	
240	1	
220		
200	Abnormal	
	Apr22/24	Apr22/24



Certificate 12367

Laboratory

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 **Sample No.** : ML0000987 Lab Number : 06159490 Unique Number : 10994913

Test Package : CONST

Received Tested Diagnosed

: 24 Apr 2024

: 25 Apr 2024 : 26 Apr 2024 - Jonathan Hester **WILLIAM HAZEL** PO BOX 600 CHANTILLY, VA US 20153

Contact: SERVICE MANAGER jimmy_elswick@wahazel.com T: (703)378-8300

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)