

OIL ANALYSIS REPORT

Area MINING ME-56 SHUTTLEWAGON SW-25 52513026A

Front Differential

Fluid CAT TDTO SAE 50 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.




SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0910926	WC0909657	WC0866105
Sample Date		Client Info		15 Apr 2024	28 Feb 2024	01 Nov 2023
Machine Age	hrs	Client Info		10300	10894	0
Oil Age	hrs	Client Info		1500	1000	500
Oil Changed		Client Info		Not Changd	Not Changd	N/A
Sample Status				NORMAL	NORMAL	ATTENTION
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	76	14	16
Chromium	ppm	ASTM D5185m		0	<1	0
Nickel	ppm	ASTM D5185m		0	<1	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	2	2
Lead	ppm	ASTM D5185m		0	<1	0
Copper	ppm	ASTM D5185m		0	<1	4
Tin			>100	۰ <1	<1	4
Vanadium	ppm	ASTM D5185m	>10	< 1	<1	0
Cadmium	ppm				<1	0
	ppm	ASTM D5185m		0		-
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		5	1	1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	2	2
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		32	28	23
Calcium	ppm	ASTM D5185m	2980	2953	2828	2817
Phosphorus	ppm	ASTM D5185m	1100	1097	1085	899
Zinc	ppm	ASTM D5185m	1270	1265	1255	1191
Sulfur	ppm	ASTM D5185m		9594	8850	5832
CONTAMINANTS	i i	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	9	9	5
Sodium	ppm	ASTM D5185m		<1	1	2
Potassium	ppm	ASTM D5185m	>20	0	1	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
5:38:32) Boy: 1					ion TRACY KE	

Contact/Location: TRACY KEE - COVCAMTN



OIL ANALYSIS REPORT



FLUID PRO	PERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D445	195	187	189	96.3	
SAMPLE IM	AGES	method	limit/base	current	history1	history2	
Color				no image	no image	no image	
Bottom				no image	no image	no image	
GRAPHS							
Ferrous Alloy	/S						
70 - iron	n		1				
60 - nickel		/					
50- E to							
통 40		/					
20-	/	/					
10-							
0	24		24				
Nov1/23	Feb28/24		Apr15/24				
Non-ferrous							
9 copper							
8 -							
6							
<u>ق</u> 5-							
4							
2							
1							
Nov1/23	Feb28/24		Apr15/24				
ĕ Viscosity @ 4			Ap				
	т о с						
220 -							
200 - Base							
180 (3-0 € 160 35	/						
왕 160 Abnormal 경 140 -			1				
120							
100							
80	4						
Nov1/23	Feb28/24		Apr15/24				
: WearCheck US	A - 501 Madis	on Ave., Carv	NC 27513		COVIA -	CAMDEN - 0	
: WC0910926	Rec	eived : 24	Apr 2024			SAND MILL F	
er : 06159498 er : 10994921	Test Diac		6 Apr 2024 Apr 2024 - W	les Davis		CAMDEN, T US 3832	
ae : CONST					Contact: TRACY KE		



 Certificate 12367
 Test Package
 : CONST

 To discuss this sample report, contact Customer Service at 1-800-237-1369.
 tra

 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: COVCAMTN [WUSCAR] 06159498 (Generated: 04/25/2024 15:38:32) Rev: 1

Contact/Location: TRACY KEE - COVCAMTN Page 2 of 2

T:

F:

tracy.kee@coviacorp.com