

# **OIL ANALYSIS REPORT**

# MAIN PLANT

**MYCOM S1** 

Refrigeration Compressor

Fluic CHEVRON CAPELLA OIL WF 68 (55 GAL)

## DIAGNOSIS

#### A Recommendation

Resample at the next service interval to monitor.

#### Wear

Area

All component wear rates are normal.

### Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.


## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0006523	USP240622	USP240625
Sample Date		Client Info		27 Sep 2023	27 Mar 2023	07 Sep 2022
Machine Age	hrs	Client Info		23769	0	20790
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	ABNORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	0	<1	<1
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	0	0	0
Tin	ppm	ASTM D5185m	>4	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	0	0	0	0
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		0	0	1
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		140	0	194
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon			>15	<1	0	<1
Sodium	ppm ppm	ASTM D5185m	>10	1	0	0
Potassium		ASTM D5185m	>20	، <1	<1	0
Water	ppm %	ASTM D5185III ASTM D6304		<1 0.002	0.003	0.004
ppm Water	<sup>7</sup> o	ASTM D0304 ASTM D6304		16	33.1	44.3
FLUID CLEANLIN		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	▲ 27848	▲ 150856	12968
Particles >6µm		ASTM D7647		3748	▲ 25130	2491
Particles >14µm		ASTM D7647	>320	36	114	70
Particles >21µm		ASTM D7647		5	8	8
Particles >38µm		ASTM D7647	>20	0	1	1
Particles >71µm		ASTM D7647 ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	0 22/19/12	4/22/14	21/18/13
FLUID DEGRADA		method	limit/base		history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974	-111100430	0.014	0.014	0.014
	mgittering			01017	0.017	0.017


Contact/Location: ? ? - LINQUI Page 1 of 2


Sample Rating Trend






# **OIL ANALYSIS REPORT**





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	64.0	74.2	65.0	78.5
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				•		S4
Bottom						

Bottom



 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

 Report Id: LINQUI [WUSCAR] 06160416 (Generated: 05/04/2024 04:22:19) Rev: 1
 Contac

Contact/Location: ? ? - LINQUI Page 2 of 2

F: