


## **OIL ANALYSIS REPORT**

## NOT GIVEN 23HE004410 - MACHINED METALS

Component



## DIAGNOSIS

## Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the


## **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM    | MATION   | method      | limit/base | current     | history1 | history2 |
|------------------|----------|-------------|------------|-------------|----------|----------|
| Sample Number    |          | Client Info |            | UCS06160479 |          |          |
| Sample Date      |          | Client Info |            | 19 Apr 2024 |          |          |
| Machine Age      | hrs      | Client Info |            | 1919        |          |          |
| Oil Age          | hrs      | Client Info |            | 0           |          |          |
| Oil Changed      |          | Client Info |            | Not Changd  |          |          |
| Sample Status    |          |             |            | NORMAL      |          |          |
| CONTAMINATIO     | V        | method      | limit/base | current     | history1 | history2 |
| Water            |          | WC Method   | >0.1       | NEG         |          |          |
| WEAR METALS      |          | method      | limit/base | current     | history1 | history2 |
| Iron             | ppm      | ASTM D5185m | >50        | 1           |          |          |
| Chromium         | ppm      | ASTM D5185m | >10        | <1          |          |          |
| Nickel           | ppm      | ASTM D5185m |            | <1          |          |          |
| Titanium         | ppm      | ASTM D5185m |            | <1          |          |          |
| Silver           | ppm      | ASTM D5185m |            | 0           |          |          |
| Aluminum         | ppm      | ASTM D5185m | >25        | 2           |          |          |
| Lead             | ppm      | ASTM D5185m | >25        | <1          |          |          |
| Copper           | ppm      | ASTM D5185m | >50        | 2           |          |          |
| Tin              | ppm      | ASTM D5185m | >15        | <1          |          |          |
| Vanadium         | ppm      | ASTM D5185m |            | <1          |          |          |
| Cadmium          | ppm      | ASTM D5185m |            | <1          |          |          |
| ADDITIVES        |          | method      | limit/base | current     | history1 | history2 |
| Boron            | ppm      | ASTM D5185m |            | 0           |          |          |
| Barium           | ppm      | ASTM D5185m |            | 6           |          |          |
| Molybdenum       | ppm      | ASTM D5185m |            | <1          |          |          |
| Manganese        | ppm      | ASTM D5185m |            | <1          |          |          |
| Magnesium        | ppm      | ASTM D5185m |            | <1          |          |          |
| Calcium          | ppm      | ASTM D5185m |            | 0           |          |          |
| Phosphorus       | ppm      | ASTM D5185m |            | 581         |          |          |
| Zinc             | ppm      | ASTM D5185m |            | 0           |          |          |
| Sulfur           | ppm      | ASTM D5185m |            | 1412        |          |          |
| CONTAMINANTS     | ;        | method      | limit/base | current     | history1 | history2 |
| Silicon          | ppm      | ASTM D5185m | >25        | 4           |          |          |
| Sodium           | ppm      | ASTM D5185m |            | 2           |          |          |
| Potassium        | ppm      | ASTM D5185m | >20        | <1          |          |          |
| FLUID DEGRADA    | ATION    | method      | limit/base | current     | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045  |            | 0.20        |          |          |


# **Sullivan**


## **OIL ANALYSIS REPORT**



| VISUAL             |   | method    | limit/base | current | history1 | history2 |
|--------------------|---|-----------|------------|---------|----------|----------|
| White Metal        | scalar                                  | *Visual   | NONE       | NONE    |          |          |
| Yellow Metal       | scalar                                  | *Visual   | NONE       | NONE    |          |          |
| Precipitate        | scalar                                  | *Visual   | NONE       | NONE    |          |          |
| Silt               | scalar                                  | *Visual   | NONE       | NONE    |          |          |
| Debris             | scalar                                  | *Visual   | NONE       | LIGHT   |          |          |
| Sand/Dirt          | scalar                                  | *Visual   | NONE       | NONE    |          |          |
| Appearance         | scalar                                  | *Visual   | NORML      | NORML   |          |          |
| Odor               | scalar                                  | *Visual   | NORML      | NORML   |          |          |
| Emulsified Water   | scalar                                  | *Visual   | >0.1       | NEG     |          |          |
| Free Water         | scalar                                  | *Visual   |            | NEG     |          |          |
| FLUID PROPERT      | TIES                                    | method    | limit/base | current | history1 | history2 |
| Visc @ 40°C        | cSt                                     | ASTM D445 |            | 42.5    |          |          |
| SAMPLE IMAGES      | S                                       | method    | limit/base | current | history1 | history2 |
| Color              |   |           |            | a       | no image | no image |
| Bottom             |   |           |            |         | no image | no image |
| GRAPHS             |   |           |            |         |          |          |
| Ferrous Alloys     |   |           |            |         |          |          |
| o iron             |   |           |            |         |          |          |
| annananan chromium |   |           |            |         |          |          |
| 4                  |   |           |            |         |          |          |
| 2                  |   |           |            |         |          |          |
| 0                  | *************************************** |           |            |         |          |          |
| Apr19/24           |   |           | Apr19/24   |         |          |          |
| Apr                |   |           | Арг        |         |          |          |











Certificate 12367

Laboratory

Sample No.

: UCS06160479 Lab Number : 06160479

Unique Number : 10995902 Test Package : IND 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Apr 2024

**Tested** : 26 Apr 2024 Diagnosed

: 26 Apr 2024 - Sean Felton

US 60160 Contact: J.P. PEDERSEN jpedersen@harrisequipment.com T: (708)343-0866

HARRIS EQUIPMENT

2040 N HAWTHORNE

MELROSE PARK, IL

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)