

OIL ANALYSIS REPORT



SMART OIL **HERTZ VD031994**

Component Compressor

\neg	$\Lambda \cap$	N 10	\sim	

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is acceptable for the time in

				Apr2024		
SAMPLE INFORI	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHK06160515		
Sample Date		Client Info		11 Apr 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		675		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	8		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	8		
Lead	ppm	ASTM D5185m	>25	<1		
Copper	ppm	ASTM D5185m	>50	3		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m	20	0		
Phosphorus	ppm	ASTM D5185m		55		
Zinc	ppm	ASTM D5185m		4		
Sulfur	ppm	ASTM D5185m		532		
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	20		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
	1/01::	4.0TH D.04 :-		.		


Acid Number (AN)

mg KOH/g ASTM D8045

0.15



OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	MODER		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	46.8		

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color		٥		no image	no image
Bottom				no image	no image

GRAPHS Ferrous Alloys











Certificate 12367

Laboratory

Sample No. : UHK06160515

Lab Number : 06160515 Unique Number : 10995938

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 25 Apr 2024 Tested

: 26 Apr 2024 Diagnosed : 26 Apr 2024 - Sean Felton

ATLANTA AIR COMPRESSOR - HERTZ 123 MERCHANTS PARK DR

HOSCHTON, GA US 30548

Contact: Service Manager

Test Package : IND 2 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: Service Manager - UCATLHER

T:

F: