

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id 80-253 Component Front Differential Fluid TDH FLUID SAE 75W80 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0936875	WC0620057	
Sample Date		Client Info		01 Mar 2024	15 Dec 2021	
Machine Age	hrs	Client Info		1055	0	
Oil Age	hrs	Client Info		0	0	
Oil Changed		Client Info		Changed	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	241	16	
Chromium	ppm	ASTM D5185m	>10	<1	<1	
Nickel	ppm	ASTM D5185m	>10	0	0	
Titanium	ppm	ASTM D5185m		2	<1	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	9	2	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>100	8	2	
Tin	ppm	ASTM D5185m	>10	<1	<1	
Antimony	ppm	ASTM D5185m	>5		0	
Vanadium	ppm	ASTM D5185m	20	<1	0	
Cadmium	ppm	ASTM D5185m		<1	0	
	ppin			_		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	10	36	385	
Barium	ppm	ASTM D5185m	10	2	0	
Molybdenum	ppm	ASTM D5185m	10	6	101	
Manganese	ppm	ASTM D5185m		2	1	
Magnesium	ppm	ASTM D5185m	100	29	491	
Calcium	ppm	ASTM D5185m	3500	3188	1544	
Phosphorus	ppm	ASTM D5185m	1150	1290	864	
Zinc	ppm	ASTM D5185m	1150	1365	973	
Sulfur	ppm	ASTM D5185m	5000	3879	2578	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	38	12	
Sodium	ppm	ASTM D5185m	210	2	2	
Potassium	ppm	ASTM D5185m	>20	16	<1	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	MODER	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>.2			
Free Water	scalar	*Visual	>.∠	NEG	NEG)n: ByEtel CALDW	



OIL ANALYSIS REPORT



	FLUID PROPERTIE	ES method	l limit/base	current	history1	history2
	Visc @ 40°C	cSt ASTM D44	45 48	52.8	62.5	
	SAMPLE IMAGES	method	l limit/base	current	history1	history2
6	Color			no image	no image	no image
Mar1/24	Bottom			no image	no image	no image
	GRAPHS					
	Ferrous Alloys		Mar1/24			
Laboratory Sample No. Lab Number Unique Number		Received : Tested :	ary, NC 27513 09 May 2024 10 May 2024 13 May 2024 - Dor			AND BRIDGE 122ND E AVE TULSA, OK US 74146



TULSA, OK US 74146 Contact: BEN CALDWELL kevin.marson@wearcheck.com T: (918)728-5749 106:2012) F:

Contact/Location: BEN CALDWELL - MANTUL