

# **OIL ANALYSIS REPORT**

Sample Rating Trend



# Machine Id

#### 13404 Component Brake Fluid {not provided} (--- GAL)

#### DIAGNOSIS

#### Recommendation

The fluid change at the time of sampling has been noted. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

### Wear

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the fluid.

#### Fluid Condition


The condition of the fluid is acceptable for the time in service.

SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0913150	WC0888144	
Sample Date		Client Info		03 May 2024	21 Mar 2024	
Machine Age	hrs	Client Info		1832	1250	
Oil Age	hrs	Client Info		582	1250	
Oil Changed		Client Info		Changed	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>350	12	8	
Chromium	ppm	ASTM D5185m	>5	<1	0	
Nickel	ppm	ASTM D5185m	>5	0	0	
Titanium	ppm	ASTM D5185m		<1	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>8	2	<1	
Lead	ppm	ASTM D5185m	>10	<1	0	
Copper	ppm	ASTM D5185m	>150	12	11	
Tin	ppm	ASTM D5185m	>5	<1	0	
Vanadium	ppm	ASTM D5185m		<1	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		68	5	
Barium	ppm	ASTM D5185m		<1	0	
Molybdenum	ppm	ASTM D5185m		2	0	
Manganese	ppm	ASTM D5185m		<1	0	
Magnesium	ppm	ASTM D5185m		28	4	
Calcium	ppm	ASTM D5185m		2650	2479	
Phosphorus	ppm	ASTM D5185m		1150	882	
Zinc	ppm	ASTM D5185m		1184	991	
Sulfur	ppm	ASTM D5185m		4820	4380	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	62	104	
Sodium	ppm	ASTM D5185m		1	4	
Potassium	ppm	ASTM D5185m	>20	1	0	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
2:21:08) Rev: 1				Contact/Loc	ation: MIKE WY	ATT - TRANEW

Report Id: TRANEW [WUSCAR] 06174390 (Generated: 05/13/2024 12:21:08) Rev: 1



# **OIL ANALYSIS REPORT**



	FLUID PROPERTIES	method				history2
	Visc @ 40°C cSt	ASTM D445		42.0	40.2	
	SAMPLE IMAGES	method	limit/base	current	history1	history2
54	Color			no image	no image	no image
May3/24	Bottom			no image	no image	no image
	GRAPHS		L			
	60 50 40 30		44 May3/24 May3			
ple No. :	WearCheck USA - 501 Madis WC0913150 Rec 06174390 Test	eived : 09 ted : 10	NC 27513 May 2024 May 2024 Jay 2024 - Dor			<b>RUCTION CO</b> DRAWER 157 EW BERN, N US 2856



mwyatt@traderconstruction.com T: (252)633-1399 M 106:2012) F: (252)638-4871

Contact: MIKE WYATT

Contact/Location: MIKE WYATT - TRANEW