

OIL ANALYSIS REPORT



Machine Id **13404** Component **Rear Differential** Fluid **TDTO FLUID SAE 30 (--- GAL)**

DIAGNOSIS

A Recommendation

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

🔺 Wear

Bearing and/or bushing wear is indicated. All other metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0888208		
Sample Date		Client Info		03 May 2024		
Machine Age	hrs	Client Info		1832		
Oil Age	hrs	Client Info		1832		
Oil Changed		Client Info		Changed		
Sample Status				ABNORMAL		
CONTAMINATION	l	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	148		
Chromium	ppm	ASTM D5185m	>10	2		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	10		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>100	<u> </u>		
Tin	ppm	ASTM D5185m	>10	1		
Vanadium	ppm	ASTM D5185m	-	<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	37	8		
Barium	ppm	ASTM D5185m	7	<1		
Molybdenum	ppm	ASTM D5185m	5	3		
Manganese	ppm	ASTM D5185m		2		
Magnesium	ppm	ASTM D5185m	40	9		
Calcium	ppm	ASTM D5185m	2650	3105		
Phosphorus	ppm	ASTM D5185m	1050	1116		
Zinc	ppm	ASTM D5185m	1075	1203		
Sulfur	ppm	ASTM D5185m	5750	8805		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	23		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	2		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water	scalar	*Visual		NEG		
:27:15) Rev: 1	Journ				ation: MIKE WY	ATT - TRANEW


Report Id: TRANEW [WUSCAR] 06174406 (Generated: 05/13/2024 12:27:15) Rev: 1

Contact/Location: MIKE WYATT - TRANEW




80 70 +72/E/kely

OIL ANALYSIS REPORT



FLUID PROPER	TIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	101	95.1		
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color				no image	no image	no image
_						
Bottom				no image	no image	no image
GRAPHS Ferrous Alloys						
			1			
0 - chromium 20 - nickel						
10 -						
0						
0						
0						
May3/24			May3/24			
≥ ∧ Non-ferrous Meta			M			
20 - copper lead						
00						
30						
50 -						
10						
0						
May3/24			May3/24			
≊ Viscosity @ 40°C			Ma			
5 Abnormal						
5						
10-						
15 - Base 10 - 9						
95						
35 -						
30 - Abnormal						
70			124			
May3/24			May3/24			
WearCheck USA - 50)1 Madisc	on Ave., Carv	, NC 27513	т	RADER CONST	RUCTION C
WC0888208 06174406	Rece Teste	ived : 09) May 2024) May 2024		POI	DRAWER 157 EW BERN, N



Report Id: TRANEW [WUSCAR] 06174406 (Generated: 05/13/2024 12:27:15) Rev: 1

Contact/Location: MIKE WYATT - TRANEW