

OIL ANALYSIS REPORT

Sample Rating Trend

VIS DEBRIS

Area CS-46 [PLC1742082] KAESER 1090 - DYKSTRA DAIRY

Component Compressor

DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Moderate concentration of visible dirt/debris present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	/IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06175612		
Sample Date		Client Info		02 May 2024		
Machine Age	hrs	Client Info		19887		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Changed		
Sample Status				MARGINAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	>3	0		
Titanium	ppm	ASTM D5185m	>3	0		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>10	0		
Lead	ppm	ASTM D5185m	>10	0		
Copper	ppm	ASTM D5185m	>50	1		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	1.5	0		
Barium	ppm	ASTM D5185m	0	<1		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m	0.3	0		
Magnesium	ppm	ASTM D5185m	0	0		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	406	127		
Zinc	ppm	ASTM D5185m	0	6		
Sulfur	ppm	ASTM D5185m	1283	1643		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.463	0.28		




OIL ANALYSIS REPORT


method

limit/base


current

VISUAL





	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE		
May2/24	Appearance	scalar	*Visual	NORML	NORML		
May	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	TIES	method	limit/ba	ase current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	47.9	46.1		
-	SAMPLE IMAGES	S	method	limit/ba	ase current	history1	history2
May2/24	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Metal	s		May224			
	Viscosity @ 40°C			May2/24	Acid Number		
	(2,0) 45 40 40 40 40 40 40 40 40 40 40			May2/24	Base Base		
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report,	: 11021665 : IND 2	Recei Teste Diagn	ved : 10 d : 13 losed : 13	24	CISCO AIR SYSTEM 214 27TH S SACRAMENTO, C US 958 Contact: BARRY FRKOVIC barryfrkovich@ciscoair.co T: (916)444-252		



Contact/Location: BARRY FRKOVICH - UCCISSAC

F: x:

history2

history1