


OIL ANALYSIS REPORT



KANSAS/44/EG - DOZER 35.13L [KANSAS^44^EG - DOZER]

Left Final Drive

MOBIL MOBILTRANS HD 50 (--- GAL)





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0918362	WC0673626	WC0585840
Sample Date		Client Info		01 May 2024	19 Sep 2022	03 Aug 2021
Machine Age	hrs	Client Info		5735	5189	4800
Oil Age	hrs	Client Info		546	4677	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	55	36	29
Chromium	ppm	ASTM D5185m	>10	3	1	1
Nickel	ppm	ASTM D5185m	>5	<1	0	0
Titanium	ppm	ASTM D5185m	>15	<1	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>75	2	2	2
Lead	ppm	ASTM D5185m	>10	<1	<1	1
Copper	ppm	ASTM D5185m	>75	2	<1	<1
Tin	ppm	ASTM D5185m	>8	<1	<1	0
Antimony	ppm	ASTM D5185m				3
Vanadium	ppm	ASTM D5185m		<1	0	<1
Cadmium	ppm	ASTM D5185m		<1	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		<1	0	15
Barium	ppm	ASTM D5185m		2	0	0
Molybdenum	ppm	ASTM D5185m		- <1	<1	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		13	12	21
Calcium	ppm	ASTM D5185m		3211	3125	3398
Phosphorus	ppm	ASTM D5185m		1185	1008	1073
Zinc	ppm	ASTM D5185m		1332	1258	1254
Sulfur	ppm	ASTM D5185m		15039	14733	13606
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	22	12	16
Sodium	ppm	ASTM D5185m		0	2	2
Potassium	ppm	ASTM D5185m	>20	3	0	12
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
	Juanun				Cubmitted Du	IVIECTIOOD


Submitted By: JAMESE MOORE





OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	195	191	197	200
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						









Certificate 12367

Laboratory

Sample No. : WC0918362 Lab Number : 06175910

Unique Number : 11021963 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 10 May 2024

Tested : 13 May 2024 Diagnosed : 13 May 2024 - Wes Davis

3219 WEST MAY ST

SHERWOOD CONSTRUCTION CO INC

WICHITA, KS US 67213 Contact: DOUG KING doug.king@sherwood.net

T: (316)617-3161

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: SHEWIC [WUSCAR] 06175910 (Generated: 05/13/2024 09:18:56) Rev: 1

Submitted By: JAMES MOORE

F: x: