

OIL ANALYSIS REPORT

Sample Rating Trend





MINING ME-15 CATERPILLAR 980G MK700428 Front Right Final Drive

SHELL Spirax S4 CX 30 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Area

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0927340	WC0927326	
Sample Date		Client Info		07 May 2024	04 Apr 2024	
Machine Age	hrs	Client Info		9245	8774	
Oil Age	hrs	Client Info		9245	0	
Oil Changed		Client Info		N/A	N/A	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>800	66	47	
Chromium	ppm	ASTM D5185m	>10	<1	1	
Nickel	ppm	ASTM D5185m	>5	0	<1	
Titanium	ppm	ASTM D5185m	>15	<1	<1	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>75	2	2	
Lead	ppm	ASTM D5185m	>10	<1	<1	
Copper	ppm	ASTM D5185m	>75	2	2	
Tin	ppm	ASTM D5185m	>8	<1	<1	
Vanadium	ppm	ASTM D5185m		<1	<1	
Cadmium	ppm	ASTM D5185m		<1	<1	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		2	0	
Barium	ppm	ASTM D5185m		2	<1	
Molybdenum	ppm	ASTM D5185m		8	7	
Manganese	ppm	ASTM D5185m		<1	1	
Magnesium	ppm	ASTM D5185m		24	24	
Calcium	ppm	ASTM D5185m		3233	3145	
Phosphorus	ppm	ASTM D5185m		1144	1162	
Zinc	ppm	ASTM D5185m		1279	1296	
Sulfur	ppm	ASTM D5185m		8800	9113	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>400	13	12	
Sodium	ppm	ASTM D5185m		0	<1	
Potassium	ppm	ASTM D5185m	>20	2	3	
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	NONE	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	
Free Water 9:12:38) Rev: 1	scalar	*Visual		NEG	NEG Submitted I	 By: Daid Hutson



OIL ANALYSIS REPORT



FLUID PROPEF Visc @ 40°C	cSt	method ASTM D445	limit/base	current 192	history1 193	history2
SAMPLE IMAG	ES	method	limit/base	current	history1	history2
Color				no imago	no imago	no imago
COIOF				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						
Ferrous Alloys						
0 - iron						
0						
Apr4/24			May7/24 -			
			May			
Non-ferrous Met	als					
9 - copper						
8 tin						
7-						
5-						
4						
2-						
1-						
74 10 10			/24			
Apr4/24			May7/24			
Viscosity @ 40°	2					
0-						
⁰ Abnormal						
0						
0-						
0 - Base						
0- Abnormal						
0						
Apr4/24			May7/24 -			
			70			
AF			×			



Report Id: COVTUS [WUSCAR] 06175940 (Generated: 05/13/2024 09:12:38) Rev: 1

Submitted By: Daid Hutson Page 2 of 2