

# **OIL ANALYSIS REPORT**

Sample Rating Trend



# Machine Id

**RK TRUCK-4/314** 

Hydraulic System Fluid AW HYDRAULIC OIL ISO 32 (--- LTR)

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

## Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The condition of the oil is acceptable for the time in service.


SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0917755	WC0790388	WC0572922
Sample Date		Client Info		22 Apr 2024	24 Apr 2023	28 Apr 2021
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	<1	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	<1	<1
Aluminum	ppm	ASTM D5185m	>10	2	2	1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	3	2	2
Tin	ppm	ASTM D5185m	>10	0	0	0
Antimony	ppm	ASTM D5185m	>10			0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium		ASTM D5185m		0	<1	0
	ppm	ASTIM D3103III		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	<1
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	0	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	25	0	2	0
Calcium	ppm	ASTM D5185m	200	24	52	53
Phosphorus	ppm	ASTM D5185m	300	331	342	323
Zinc	ppm	ASTM D5185m	370	441	435	380
Sulfur	ppm	ASTM D5185m	2500	884	1233	812
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	<1	<1	0
Sodium	ppm	ASTM D5185m		2	<1	2
Potassium	ppm	ASTM D5185m	>20	<1	1	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual	-	NEG	MESNE ONTER/	1 - GOFCOLCO
						Page 1 of 2



# **OIL ANALYSIS REPORT**



FLUID PROPE	RTIES	method	limit/base	current	history1	history
∕isc @ 40°C	cSt	ASTM D445	32	32.9	32.7	32.8
SAMPLE IMAG	ES	method	limit/base	current	history1	history
Color			-	no image	no image	no image
Bottom				no image	no image	no image
GRAPHS			L			1
Ferrous Alloys						
iron chromium						
nickel						
Jun1/10 Jun3/12 Jun4/14	Jun7/16	Apr18/18 - Apr29/20 -	Apr24/23			
Non-ferrous Me	tals					
copper						
• • • • • • • • • • • • • • • • • • •						
Lt		~	/			
	-	$\overline{\mathcal{A}}$				
Jun1/10 Jun3/12 Jun4/14	Jun7/16 -	Apr18/18 Apr29/20	Apr24/23			
Viscosity @ 40°	С					
Abnormal						
$\sim$						
Base			-			
Abnormal						
Jun1/10	Jun7/16	8/18	4/23			
Jun1/10 Jun3/12 Jun4/14	Jun	Apr18/18 Apr29/20	Apr24/23			



Contact/Location: JAMES MONTERA - COLCOLCO

Page 2 of 2