




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
PRESS 7
 Component
Hydraulic System
 Fluid
 {not provided} (500 GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORMATION | | method | limit/base | current | history1 | history2 |
|--------------------|-------------|-------------|------------|--------------------|-------------|----------|
| Sample Number | Client Info | | | PH0003836 | PH0000783 | --- |
| Sample Date | Client Info | | | 12 May 2024 | 23 Jul 2023 | --- |
| Machine Age | mths | Client Info | | 0 | 0 | --- |
| Oil Age | mths | Client Info | | 0 | 18 | --- |
| Oil Changed | Client Info | | | N/A | Filtered | --- |
| Sample Status | | | | NORMAL | NORMAL | --- |

| CONTAMINATION | | method | limit/base | current | history1 | history2 |
|---------------|-----------|--------|------------|------------|----------|----------|
| Water | WC Method | | >0.05 | NEG | NEG | --- |


| WEAR METALS | | method | limit/base | current | history1 | history2 |
|-------------|-----|-------------|------------|--------------|----------|----------|
| Iron | ppm | ASTM D5185m | >20 | <1 | 1 | --- |
| Chromium | ppm | ASTM D5185m | >20 | 0 | 0 | --- |
| Nickel | ppm | ASTM D5185m | >20 | 0 | 0 | --- |
| Titanium | ppm | ASTM D5185m | | 0 | 0 | --- |
| Silver | ppm | ASTM D5185m | | 0 | 0 | --- |
| Aluminum | ppm | ASTM D5185m | >20 | 0 | <1 | --- |
| Lead | ppm | ASTM D5185m | >20 | 0 | 0 | --- |
| Copper | ppm | ASTM D5185m | >20 | 5 | <1 | --- |
| Tin | ppm | ASTM D5185m | >20 | <1 | <1 | --- |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | --- |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | --- |

| ADDITIVES | | method | limit/base | current | history1 | history2 |
|------------|-----|-------------|------------|-------------|----------|----------|
| Boron | ppm | ASTM D5185m | | 0 | 0 | --- |
| Barium | ppm | ASTM D5185m | | 0 | 0 | --- |
| Molybdenum | ppm | ASTM D5185m | | 0 | <1 | --- |
| Manganese | ppm | ASTM D5185m | | 1 | <1 | --- |
| Magnesium | ppm | ASTM D5185m | | 139 | 136 | --- |
| Calcium | ppm | ASTM D5185m | | 715 | 660 | --- |
| Phosphorus | ppm | ASTM D5185m | | 328 | 303 | --- |
| Zinc | ppm | ASTM D5185m | | 376 | 384 | --- |
| Sulfur | ppm | ASTM D5185m | | 3546 | 3759 | --- |

| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
|--------------|-----|-------------|------------|--------------|----------|----------|
| Silicon | ppm | ASTM D5185m | >15 | <1 | <1 | --- |
| Sodium | ppm | ASTM D5185m | | 2 | 0 | --- |
| Potassium | ppm | ASTM D5185m | >20 | 0 | 2 | --- |





| FLUID CLEANLINESS | | method | limit/base | current | history1 | history2 |
|-------------------|--|--------------|------------|-----------------|----------|----------|
| Particles >4µm | | ASTM D7647 | >10000 | 1038 | 2191 | --- |
| Particles >6µm | | ASTM D7647 | >2500 | 296 | 607 | --- |
| Particles >14µm | | ASTM D7647 | >320 | 32 | 82 | --- |
| Particles >21µm | | ASTM D7647 | >80 | 14 | 29 | --- |
| Particles >38µm | | ASTM D7647 | >20 | 1 | 3 | --- |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 1 | --- |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | 17/15/12 | 18/16/14 | --- |

| FLUID DEGRADATION | | method | limit/base | current | history1 | history2 |
|-------------------|----------|------------|------------|--------------|----------|----------|
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | 0.646 | 0.56 | --- |






OIL ANALYSIS REPORT








| VISUAL | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- |
| Precipitate | scalar | *Visual | NONE | NONE | --- |
| Silt | scalar | *Visual | NONE | NONE | --- |
| Debris | scalar | *Visual | NONE | NONE | LIGHT |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- |
| Odor | scalar | *Visual | NORML | NORML | --- |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | --- |
| Free Water | scalar | *Visual | | NEG | --- |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| Visc @ 40°C | cSt | ASTM D445 | 45.1 | 45.4 | --- |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---------------|--------|------------|---------|----------|----------|
|---------------|--------|------------|---------|----------|----------|



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : PH0003836 **Received** : 13 May 2024
Lab Number : 06177104 **Tested** : 16 May 2024
Unique Number : 11023157 **Diagnosed** : 16 May 2024 - Angela Borella
Test Package : PLANT (Additional Tests: PrtFilter)

WEBASTO
 55111 GRAND RIVER RD
 NEW HUDSON, MI
 US 48165
 Contact: TIM ELKINS
 timothy.elkins@webasto.com
 T: (248)513-7408
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)