

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

Area CZ-20 [PM6-2696089] ATLAS COPCO API791577 - APPLE

Component Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	1ATI <u>ON</u>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06177301		
Sample Date		Client Info		24 Apr 2024		
Machine Age	hrs	Client Info		18403		
Oil Age	hrs	Client Info		3100		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
			11 1. 0			
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	2		
Chromium	ppm	ASTM D5185m	>5	<1		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>15	2		
Lead	ppm	ASTM D5185m	>65	<1		
Copper	ppm	ASTM D5185m	>65	<1		
Tin	ppm	ASTM D5185m	>10	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		3		
Phosphorus	ppm	ASTM D5185m		183		
Zinc	ppm	ASTM D5185m		12		
Sulfur	ppm	ASTM D5185m		399		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2



OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Apr24/24	Appearance	scalar	*Visual	NORML	NORML			
Ap	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	IES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445		71.8			
	SAMPLE IMAGES	3	method	limit/base	current	history1	history2	
Api24/24 +	Color					no image	no image	
	Bottom					no image	no image	
	Ferrous Alloys			Apr24/24				
	Viscosity @ 40-C			Apr24/24 Acid Number (mg KOH(g) 0.0 Acid Number (mg KOH(g)	Acid Number			
Laboratory Sample No. Lab Number Unique Number Test Package discuss this sample report,	: WearCheck USA - 50 : UCH06177301 : 06177301 : 11023354 : IND 2 contact Customer Serve	Rece Teste Diagr	son Ave., Cary, NC 27513 eived : 13 May 2024 ted : 14 May 2024 gnosed : 15 May 2024 - Don Baldridge			CISCO AIR SYSTEM 214 27TH S SACRAMENTO, C US 9581 Contact: BARRY FRKOVIC barryfrkovich@ciscoair.cor T: (916)444-252		

Contact/Location: BARRY FRKOVICH - UCCISSAC