

# **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

## Area NOT GIVEN [8496] INGERSOLL RAND MOX1001402

Component Compressor

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the oil.


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	<b>IATION</b>	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06177313		
Sample Date		Client Info		23 Apr 2024		
Machine Age	hrs	Client Info		396		
Oil Age	hrs	Client Info		396		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>0.8	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	2		
Lead	ppm	ASTM D5185m	>25	<1		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	2	0		
Barium	ppm	ASTM D5185m	525	413		
Molybdenum	ppm	ASTM D5185m	10	<1		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	5	2		
Calcium	ppm	ASTM D5185m	10	4		
Phosphorus	ppm	ASTM D5185m	250	133		
Zinc	ppm	ASTM D5185m	100	33		
Sulfur	ppm	ASTM D5185m	400	364		
CONTAMINANTS	5	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1		
Sodium	ppm	ASTM D5185m		8		
Potassium	ppm	ASTM D5185m	>20	3		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.21		



# **OIL ANALYSIS REPORT**



	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
Apr23/24	Appearance	scalar	*Visual	NORML	NORML		
Apr2	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.8	NEG		
	Free Water	scalar	*Visual		NEG		
	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	46	48.5		
-	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Apr23/24 +	Color				•	no image	no image
	Bottom					no image	no image
	Non-ferrous Metals	s		Apr23/24 B			
	Viscosity @ 40°C			25.0 0.2 0.2 0.2 0.1 0.1 0.1 0.0 0.0 0.0 0.0 0.0 0.0 0.0	Acid Number		
Laboratory Sample No. Lab Number Unique Number	: WearCheck USA - 501 Madison Ave., Cary, NC 27513 ADVANCED COMPRES : UCH06177313 Received : 13 May 2024 9421 F : 06177313 Tested : 14 May 2024 : 11023366 Diagnosed : 15 May 2024 - Don Baldridge						Solutions (ACA 0 RD BLDG 2 TOMBALL, T US 7737
icate 12367 Test Package liscuss this sample report, enotes test methods that	: IND 2 contact Customer Servi	ce at 1-8		-	-	Contact advancedcomp	: JIM SUARE

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: JIM SUAREZ - UCADVTOM