

OIL ANALYSIS REPORT

Sample Rating Trend



Area Conveyor 23A Conveyor Gearbox

Fluic SCHAEFFER 293A SUPREME GEAR LUBE NO TACK 220 (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.


Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0936834		
Sample Date		Client Info		09 May 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	48		
Chromium	ppm	ASTM D5185m	>10	<1		
Nickel	ppm	ASTM D5185m	>10	<1		
Titanium	ppm	ASTM D5185m		1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m		10		
Lead	ppm	ASTM D5185m		0		
Copper	ppm	ASTM D5185m		<1		
Tin	ppm	ASTM D5185m		<1		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		<1		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		51		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		424		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		6		
Calcium	ppm	ASTM D5185m		31		
Phosphorus	ppm	ASTM D5185m		1190		
Zinc	ppm	ASTM D5185m		16		
Sulfur	ppm	ASTM D5185m		27735		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		29		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	3		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		2.85		





OIL ANALYSIS REPORT



	VISUAL		method	limit/base	current	history1	history2
1	White Metal	scalar	*Visual	NONE	NONE		
	Yellow Metal	scalar	*Visual	NONE	NONE		
	Precipitate	scalar	*Visual	NONE	NONE		
	Silt	scalar	*Visual	NONE	NONE		
	Debris	scalar	*Visual	NONE	NONE		
	Sand/Dirt	scalar	*Visual	NONE	NONE		
May9/24	Appearance	scalar	*Visual	NORML	NORML		
Mar	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.2	NEG		
1	Free Water	scalar	*Visual		NEG		
	FLUID PROPE	RTIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	213	207		
	SAMPLE IMAG	ES	method	limit/base	current	history1	history2
May3/24	Color					no image	no image
	Bottom					no image	no image
	Non-ferrous Me	tals		May9/24			
	E 6 4 2 -						
	UL HAR STREAM	с		May9/24	Acid Numbe	r	
	240 230 2220 8 2220 8 3 210			(B) B) Acid Number (mg KOH() Acid Number (mg KOH)			
	200 Abnormal 190 4706/kew			May9/24 Acid Nun	May9/24		
tory No. mber	: WearCheck USA - : WC0936834 : 06177803 : 11029129	501 Madisc Rece Teste Diagi	ived : 13 ed : 14				- PITTSBOR 4191 NC 87 <i>I</i> ONCURE, N

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Submitted By: JORDAN TUTEN Page 2 of 2

T:

F: