

OIL ANALYSIS REPORT

Area CONSTRUCTORS, INC Machine Id 010091

Rear Differential Fluid MOBIL MOBILUBE SHC 75W140 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.



Sample Rating Trend



NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		SBP0007151		
Sample Date		Client Info		09 May 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		4550		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water	N	WC Method	>.2	NEG	TIIStOLA	THSTOLY2
				-		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>1200	86		
Chromium	ppm		>8	<1		
Nickel	ppm	ASTM D5185m	>20	4		
Titanium	ppm	ASTM D5185m	>4	0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>30	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	0		
Tin	ppm	ASTM D5185m	>5	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		217		
Barium	ppm	ASTM D5185m		2		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		1		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		13		
Phosphorus	ppm	ASTM D5185m		1452		
Zinc	ppm	ASTM D5185m		2		
Sulfur	ppm	ASTM D5185m		25276		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>230	160		
Sodium	ppm	ASTM D5185m		1		
Potassium	ppm	ASTM D5185m	>20	<1		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water	scalar	*Visual		NEG		
E 00 40 D					O de se la de D	I A HALL A ALL A ALL



OIL ANALYSIS REPORT

Viscosity @ 40°C



Visc @ 40°C	cSt	method ASTM D445	limit/base	current 169	history1	history2
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
Dottom				no image	nomage	no image
GRAPHS						
Ferrous Alloys						
0 - chromium 0 - nickel						
0						
D						
0 -						
0		*****				
May9/24			May9/24			
			Ma			
Non-ferrous Meta	ls					
9 - copper						
8 tin						
7-						
5-						
4						
3						
1-						
24 124			/24			
May9/24			May9/24			
Viscosity @ 40°C						
Abnormal						
0						
D + Base						
0 -						
0 +						
Abnormal						
May9/24			May9/24 -			
May			Mar			

