

OIL ANALYSIS REPORT



Machine Id 4548-3

Component 3 Gearbox

Fluid CASTROL OPTIGEAR SYNTHETIC RO 150 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please note that this is a corrected copy for data entry update for oil type.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM | /IATION | method | limit/base | current | history1 | history2 |
|------------------|----------|-------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | WC0920075 | | |
| Sample Date | | Client Info | | 12 Apr 2024 | | |
| Machine Age | mls | Client Info | | 61075 | | |
| Oil Age | mls | Client Info | | 11075 | | |
| Oil Changed | | Client Info | | Changed | | |
| Sample Status | | | | NORMAL | | |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >200 | 6 | | |
| Chromium | ppm | ASTM D5185m | >10 | <1 | | |
| Nickel | ppm | ASTM D5185m | >10 | <1 | | |
| Titanium | ppm | ASTM D5185m | | <1 | | |
| Silver | ppm | ASTM D5185m | | 0 | | |
| Aluminum | ppm | ASTM D5185m | >25 | 7 | | |
| Lead | ppm | ASTM D5185m | >50 | 0 | | |
| Copper | ppm | ASTM D5185m | >200 | 2 | | |
| Tin | ppm | ASTM D5185m | >10 | 0 | | |
| Vanadium | ppm | ASTM D5185m | | <1 | | |
| Cadmium | ppm | ASTM D5185m | | <1 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | | |
| Barium | ppm | ASTM D5185m | | 4 | | |
| Molybdenum | ppm | ASTM D5185m | | 812 | | |
| Manganese | ppm | ASTM D5185m | | 0 | | |
| Magnesium | ppm | ASTM D5185m | | <1 | | |
| Calcium | ppm | ASTM D5185m | | 216 | | |
| Phosphorus | ppm | ASTM D5185m | | 175 | | |
| Zinc | ppm | ASTM D5185m | | 4 | | |
| Sulfur | ppm | ASTM D5185m | | 14631 | | |
| CONTAMINANTS | ; | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | 15 | | |
| Sodium | ppm | ASTM D5185m | | 3 | | |
| Potassium | ppm | ASTM D5185m | >20 | 2 | | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | 0.85 | | |



OIL ANALYSIS REPORT

VISUAL



| Apri 224 | White Metal Yellow Metal Precipitate Silt Debris Sand/Dirt Appearance Odor Emulsified Water Free Water FLUID PROPERT Visc @ 40°C SAMPLE IMAGES | cSt | *Visual *Visual *Visual *Visual *Visual *Visual *Visual *Visual *Visual method ASTM D445 method | NONE NONE NONE NONE NORML NORML >0.2 limit/base limit/base | NONE NONE LIGHT NONE NORML NORML NEG NEG Current 156 current | history1 history1 history1 | history2 history2 | |
|--|--|--|--|--|--|--|---|--|
| Apri 2/24 | Color | | | | no image | no image | no image | |
| | Bottom | | | | no image | no image | no image | |
| | Abnormal | | | 4pr12/24 | Chromium (p | +2721uay Chromium (ppm) Severe Abnormal | | |
| | Copper (ppm) | | | Apri224 Apri224 | 0 - Abnormal | | Apri 224 | |
| | Viscosity @ 40°C | | | Apr12/24 | Acid Number | | An1224 - | |
| Laboratory Sample No. Lab Number Unique Number Test Package o discuss this sample report. - Denotes test methods that tatements of conformity to sp | : 11030294 : MOB 2 ; contact Customer Serv are outside of the ISO 1 | Recei Teste Diagn tice at 1-8 7025 sco | ved : 14 d : 05 losed : 05 00-237-1369 pe of accred | May 2024 5 Jun 2024 Jun 2024 - Do 9. 9. | ug Bogart | Contact: E david.gilbert@al | RK TURNPIKE KEARNY, NJ US 07032 DAVE GILBERT | |

Contact/Location: DAVE GILBERT - NEWKEA