


OIL ANALYSIS REPORT





VOLVO A35G 342028 ^{Component} Front Axle

Fluid VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0001943	VCP407241	VCP389088
Sample Date		Client Info		09 May 2024	30 Nov 2023	27 Oct 2022
Machine Age	hrs	Client Info		9138	8454	7328
Oil Age	hrs	Client Info		684	0	800
Oil Changed		Client Info		N/A	Changed	Not Changd
Sample Status				NORMAL	ATTENTION	ATTENTION
CONTAMINATION	٧	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>900	88	143	270
Chromium	ppm	ASTM D5185m	>20	1	1	4
Nickel	ppm	ASTM D5185m	>10	0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	0	2	2
Lead	ppm	ASTM D5185m	>50	0	0	0
Copper	ppm	ASTM D5185m	>150	<1	4	2
Tin	ppm	ASTM D5185m	>20	0	0	0
Antimony	ppm	ASTM D5185m	>5			
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		353	260	255
Barium	ppm	ASTM D5185m		0	2	2
Molybdenum	ppm	ASTM D5185m		1	2	4
Manganese	ppm	ASTM D5185m		3	5	10
Magnesium	ppm	ASTM D5185m		<1	4	3
Calcium	ppm	ASTM D5185m		13	41	26
Phosphorus	ppm	ASTM D5185m		2373	2285	2403
Zinc	ppm	ASTM D5185m		10	25	21
Sulfur	ppm	ASTM D5185m		31027	40894	32700
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	2	2	4
Sodium	ppm	ASTM D5185m		2	4	3
Potassium	ppm	ASTM D5185m	>20	<1	0	1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	LIGHT	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	VLITE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	ted Hye Service	Alex Adderson



OIL ANALYSIS REPORT



FLUID PROPER	TIES	method	limit/base	current	history1	histe
Visc @ 40°C	cSt	ASTM D445		57.2	50.3	49.1
SAMPLE IMAGE	ES	method	limit/base	current	history1	histo
Color				no image	no image	no ima
Bottom				no image	no image	no im
GRAPHS						
Ferrous Alloys						
300 250						
2.30 neessaan nickel						
200						
<u></u> <u>E</u> 150 -						
100			/			
50-						
72 72 0		/23	/24			
Sep3/20 0ct27/22		Nov30/23	May9/24			
Non-ferrous Met	als					
9 - copper lead						
8 tin						
6- 틆 5-						
E. 5- 4-						
3		\frown				
1- And a state of the state of						
0 0 0 0 0 0 0 0 0 0 0 0		0/23	May9/24			
0		Nav30/23	May			
Viscosity @ 40°C	2					
90 - Abnormal						
85						
2 ⁷⁵						
⊖75 € 70 ⁸ 65						
60 Abnormal						
55						
		Nov30/23 +	May9/24			
Sep 3/20						



Unique Number : 11030555 Diagnosed : 16 May 2024 - Don Baldridge Contact: KYLE RATLIFFE Test Package : CONST Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369. KRATLIFFE@MCCLUNG-LOGAN.COM * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Report Id: VOLVO8882 [WUSCAR] 06179229 (Generated: 05/16/2024 16:10:04) Rev: 1

Submitted By: Service - Alex Anderson

F: (804)266-1611

US 23060

T: