


OIL ANALYSIS REPORT

Sample Rating Trend









VOLVO A35G 342028

Component
Drop Box

VOLVO SUPER GEAR OIL 75W-80-GO102 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil


Fluid Condition

The condition of the oil is acceptable for the time in service.

. 7511-00-00 102 (UAL)			7916060		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ML0001944	VCP423663	VCP401294
Sample Date		Client Info		09 May 2024	12 Apr 2023	18 Jan 2023
Machine Age	hrs	Client Info		9138	8014	7618
Oil Age	hrs	Client Info		1124	0	0
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	83	45	57
Chromium	ppm	ASTM D5185m	>20	<1	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>30	5	<1	3
Lead	ppm	ASTM D5185m	>30	0	0	0
Copper	ppm	ASTM D5185m		1	0	<1
Tin	ppm	ASTM D5185m	>20	0	0	0
Vanadium		ASTM D5185m	<i>></i> LU	<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	' '	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		247	313	253
Barium	ppm	ASTM D5185m		0	0	1
Molybdenum	ppm	ASTM D5185m		2	<1	2
Manganese		ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		1	8	2
<u> </u>	ppm	ASTM D5185m		10	40	19
Calcium	ppm					
Phosphorus	ppm	ASTM D5185m		2543	2581	2076
Zinc	ppm	ASTM D5185m		34	21	17
Sulfur	ppm	ASTM D5185m		33263	25056	23610
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	6	2	5
Sodium	ppm	ASTM D5185m		2	2	0
Potassium	ppm	ASTM D5185m	>20	<1	2	<1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	MODER	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG





OIL ANALYSIS REPORT



FLUID PROPE	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		51.9	49.8	50.6
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image
GRAPHS						

Ferrous Alloys 350 250 100







Certificate 12367

Sample No. : ML0001944 Lab Number : 06179230 Unique Number : 11030556 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Received : 14 May 2024 **Tested** : 15 May 2024 Diagnosed : 16 May 2024 - Don Baldridge

1345 MOUNTAIN ROAD GLEN ALLEN, VA US 23060

Contact: KYLE RATLIFFE KRATLIFFE@MCCLUNG-LOGAN.COM

MCCLUNG-LOGAN EQUIPMENT CO - RICHMOND

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: Service - Alex Anderson

F: (804)266-1611