


# **OIL ANALYSIS REPORT**

Area

# HOTLINE/170 REVERSING MILL 170 BOWSER LUBE RESERVOIR 1411-032-0040

**Hydraulic System** 

PETRO CANADA HYDREX AW 68 (--- GAL)



## DIAGNOSIS

### Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.

## Contamination

There is a high amount of silt (particulates < 14 microns in size) present in the oil.

#### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

| SAMPLE INFORM   | MATION | method       | limit/base | current         | history1         | history2                        |
|-----------------|--------|--------------|------------|-----------------|------------------|---------------------------------|
| Sample Number   |        | Client Info  |            | KFS0004795      | KFS0005151       | KFS0003442                      |
| Sample Date     |        | Client Info  |            | 10 May 2024     | 19 Dec 2023      | 29 Mar 2023                     |
| Machine Age     | hrs    | Client Info  |            | 0               | 0                | 0                               |
| Oil Age         | hrs    | Client Info  |            | 0               | 0                | 0                               |
| Oil Changed     |        | Client Info  |            | N/A             | N/A              | N/A                             |
| Sample Status   |        |              |            | ABNORMAL        | ABNORMAL         | ABNORMAL                        |
| CONTAMINATION   | V      | method       | limit/base | current         | history1         | history2                        |
| Water           |        | WC Method    | >0.05      | NEG             | NEG              | NEG                             |
| WEAR METALS     |        | method       | limit/base | current         | history1         | history2                        |
| Iron            | ppm    | ASTM D5185m  | >20        | 26              | 24               | 30                              |
| Chromium        | ppm    | ASTM D5185m  | >20        | 0               | <1               | 0                               |
| Nickel          | ppm    | ASTM D5185m  | >20        | <1              | 0                | 0                               |
| Titanium        | ppm    | ASTM D5185m  |            | 0               | 0                | 0                               |
| Silver          | ppm    | ASTM D5185m  |            | 0               | 0                | 0                               |
| Aluminum        | ppm    | ASTM D5185m  | >20        | <1              | 2                | 1                               |
| Lead            | ppm    | ASTM D5185m  | >20        | 20              | 23               | 22                              |
| Copper          | ppm    | ASTM D5185m  | >20        | 10              | 13               | 12                              |
| Tin             | ppm    | ASTM D5185m  | >20        | 6               | 5                | 4                               |
| Vanadium        | ppm    | ASTM D5185m  |            | 0               | 0                | 0                               |
| Cadmium         | ppm    | ASTM D5185m  |            | <1              | 0                | 0                               |
| ADDITIVES       |        | method       | limit/base | current         | history1         | history2                        |
| Boron           | ppm    | ASTM D5185m  | 0          | 0               | 0                | 0                               |
| Barium          | ppm    | ASTM D5185m  | 0          | <1              | 0                | 0                               |
| Molybdenum      | ppm    | ASTM D5185m  | 0          | 0               | 0                | 0                               |
| Manganese       | ppm    | ASTM D5185m  | 0          | <1              | 0                | <1                              |
| Magnesium       | ppm    | ASTM D5185m  | 0          | 4               | 3                | 3                               |
| Calcium         | ppm    | ASTM D5185m  | 50         | 60              | 62               | 59                              |
| Phosphorus      | ppm    | ASTM D5185m  | 330        | 362             | 384              | 356                             |
| Zinc            | ppm    | ASTM D5185m  | 430        | 452             | 454              | 408                             |
| Sulfur          | ppm    | ASTM D5185m  | 760        | 1068            | 1012             | 686                             |
| CONTAMINANTS    | ;      | method       | limit/base | current         | history1         | history2                        |
| Silicon         | ppm    | ASTM D5185m  | >15        | <1              | 2                | <1                              |
| Sodium          | ppm    | ASTM D5185m  |            | 1               | 0                | 0                               |
| Potassium       | ppm    | ASTM D5185m  | >20        | 2               | <1               | 0                               |
| FLUID CLEANLIN  | IESS   | method       | limit/base | current         | history1         | history2                        |
| Particles >4μm  |        | ASTM D7647   | >5000      | <u>▲</u> 57931  | <b>▲</b> 44812   | <u>▲</u> 62441                  |
| Particles >6µm  |        | ASTM D7647   | >1300      | <u> </u>        | <u>▲</u> 1585    | <u>^</u> 2137                   |
| Particles >14μm |        | ASTM D7647   | >160       | 16              | 56               | 12                              |
| Particles >21µm |        | ASTM D7647   | >40        | 3               | 14               | 1                               |
| Particles >38μm |        | ASTM D7647   | >10        | 0               | 1                | 0                               |
| Particles >71μm |        | ASTM D7647   | >3         | 0               | 0                | 0                               |
| Oil Cleanliness |        | ISO 4406 (c) | >19/17/14  | <b>23/18/11</b> | <b>2</b> 3/18/13 | <u>\$\rightarrow\$ 23/18/11</u> |
| FLUID DEGRADA   | ATION  | method       | limit/base | current         | history1         | history2                        |

Acid Number (AN)

mg KOH/g ASTM D8045 0.60

0.60

0.30


0.31


/2024 10:06:14\ Dov: 1


Submitted By: COLD MILL - Josh Edwards




## **OIL ANALYSIS REPORT**










| VISUAL                  |        | method    | limit/base | current | history1 | history2 |
|-------------------------|--------|-----------|------------|---------|----------|----------|
| White Metal             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Yellow Metal            | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Precipitate             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Silt                    | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Debris                  | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Sand/Dirt               | scalar | *Visual   | NONE       | NONE    | NONE     | NONE     |
| Appearance              | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| Odor                    | scalar | *Visual   | NORML      | NORML   | NORML    | NORML    |
| <b>Emulsified Water</b> | scalar | *Visual   | >0.05      | NEG     | NEG      | NEG      |
| Free Water              | scalar | *Visual   |            | NEG     | NEG      | NEG      |
| FLUID PROPERTIES        |        | method    | limit/base | current | history1 | history2 |
| Visc @ 40°C             | cSt    | ASTM D445 | 67.4       | 69.7    | 69.6     | 66.0     |
| SAMPLE IMAGES           |        | method    | limit/base | current | history1 | history2 |
| Color                   |        |           |            |         |          | NOW.     |







Laboratory Sample No.

: KFS0004795 Lab Number : 06179346 Unique Number : 11030672

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

**Bottom** 

Received **Tested** 

: 14 May 2024 : 16 May 2024

Diagnosed : 16 May 2024 - Angela Borella

Test Package : IND 2 Certificate 12367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

**CONSTELLIUM** 

4805 SECOND STREET MUSCLE SHOALS, AL US 35661

Contact: Joel Even joel.even@constellium.com

T: (256)740-7490

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)