

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id **CATERPILLAR 745D 13408 Center Differential**

Fluid {not provided} (--- GAL)

DIAGNOSIS

Recommendation

The oil change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

A Wear

Bearing and/or bushing wear is indicated. All other metal levels are typical for a new component breaking in.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

SIS REPC	RT					WEAR
10/00 (C/N 9Ter	165001					
13408 (S/N 3T60	10520)					
L)				May2024		
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0913069		
Sample Date		Client Info		08 May 2024		
Machine Age	hrs	Client Info		2253		
Oil Age	hrs	Client Info		2253		
Oil Changed		Client Info		Changed		
Sample Status				ABNORMAL		
CONTAMINATION	N	method	limit/base	current	history1	history2
Water		WC Method	>.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	170		
Chromium	ppm	ASTM D5185m		2		
Nickel	ppm	ASTM D5185m	>3	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>2	0		
Aluminum	ppm	ASTM D5185m	>30	10		
Lead	ppm	ASTM D5185m	>13	3		
Copper	ppm	ASTM D5185m	>103	<u> </u>		
Tin	ppm	ASTM D5185m	>5	6		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		<1		
Molybdenum	ppm	ASTM D5185m		2		
Manganese	ppm	ASTM D5185m		3		
Magnesium	ppm	ASTM D5185m		10		
Calcium	ppm	ASTM D5185m		3140		
Phosphorus	ppm	ASTM D5185m		1037		
Zinc	ppm	ASTM D5185m		1236		
Sulfur	ppm	ASTM D5185m		9570		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>100	24		
Sodium	ppm	ASTM D5185m		2		
Potassium	ppm	ASTM D5185m	>20	0		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>.2	NEG		
Free Water	scalar	*Visual		NEG		
9·12·02) Rev: 1				Contact/Loc	ation MIKE W/V	ATT - TRANEW

Report Id: TRANEW [WUSCAR] 06180491 (Generated: 05/17/2024 19:12:02) Rev: 1

Contact/Location: MIKE WYATT - TRANEW



120

(100 CSt (40°C)

OIL ANALYSIS REPORT

cSt

method

ASTM D445

limit/base

current


94.9

history1


FLUID PROPERTIES

Visc @ 40°C

Non-ferrous Metals 250 T -----



SAMPLE IMAGES	method	limit/base	current	history1	history2
Color			no image	no image	no image
Bottom			no image	no image	no image
GRAPHS					
Ferrous Alloys					
140 120 <u><u><u></u></u> <u></u> <u></u> <u></u> <u></u> <u></u> <u></u> 100 <u></u> <u></u> 80</u>					
60 40 20					
0 //ay8/24		May8/24			
A Non-ferrous Metals	;				
200 + tin tin 150 +					
Б. 100-					
50-					
0 May8/24		May8/24			
Viscosity @ 40°C					
120 115 110					
日 日 日 日 日 日 日 日 日 日 日 日 日 日 日 日 日 日 日					
90 85 80 - Abnormal					
80 + 0 75 + + + 2/8/keW		May8/24			
~		~			



Report Id: TRANEW [WUSCAR] 06180491 (Generated: 05/17/2024 19:12:02) Rev: 1

Contact/Location: MIKE WYATT - TRANEW

Page 2 of 2

history2