

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id V-936 Component Right Final Drive Fluid GEAR OIL SAE 80W90 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0900243		
Sample Date		Client Info		14 May 2024		
Machine Age	hrs	Client Info		690		
Oil Age	hrs	Client Info		690		
Oil Changed		Client Info		Changed		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>500	246		
Chromium	ppm	ASTM D5185m	>10	7		
Nickel	ppm	ASTM D5185m	>10	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	12		
Tin	ppm	ASTM D5185m	>10	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	400	0		
Barium	ppm	ASTM D5185m	200	2		
Molybdenum	ppm	ASTM D5185m	12	<1		
Manganese	ppm	ASTM D5185m		6		
Magnesium	ppm	ASTM D5185m	12	2		
Calcium	ppm	ASTM D5185m	150	29		
Phosphorus	ppm	ASTM D5185m	1650	404		
Zinc	ppm	ASTM D5185m	125	30		
Sulfur	ppm	ASTM D5185m	22500	25589		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>75	4		
Sodium	ppm	ASTM D5185m	>170	6		
Potassium	ppm	ASTM D5185m	>20	12		
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
	scalar	*Visual	NONE	NONE		
Sand/Dirt						
Sand/Dirt Appearance	scalar	*Visual	NORML	NORML		
Appearance	scalar scalar	*Visual *Visual	NORML NORML	NORML NORML		



OIL ANALYSIS REPORT



	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	143	196		
	SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
	Color				no image	no image	no image
4/24							
May14/24	Bottom						
	вощот				no image	no image	no image
	GRAPHS						
	Ferrous Alloys						
	250 iron chromium						
	200 - nickel						
-	150-						
	<u>۾</u> 100 -						
	50						
	50						
	4/24 to 0		************************	⁴ /24			
	May14/24			May14/24			
	Non-ferrous Met	als					
	10 - copper						
	8						
	ق 6 -						
	4						
	2 -						
	0						
	May14/24 -			May14/24			
	్ Viscosity @ 40°C			Mar			
	200						
	190 - Abnormal						
	170						
	있 160 - 정 150 -						
	140 Base						
	130						
	120 Abnormal						
	May14/24			May14/24 -			
	Ma			Mar			
tory	: WearCheck USA - 5	01 Madiso	on Ave Carv	. NC 27513		DI	JKE LAZZAR
No.	: WC0900243	Recei	ived :15	5 May 2024			ETTEVILLE R
mber lumber	: <mark>06180518</mark> : 11031844	Teste Diagr		6 May 2024 May 2024 - W	Ves Davis		RALEIGH, N US 2760
	: CONST	2				Contac	t: NICK DIXO

To discuss this sample * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Page 2 of 2

F: